



SCIREA Journal of Physics

ISSN: 2706-8862

<http://www.scirea.org/journal/Physics>

June 12, 2023

Volume 8, Issue 3, June 2023

<https://doi.org/10.54647/physics140553>

Accurate expressions for optical coefficients, given in n(p)-type degenerate InP-crystals, due to the impurity-size effect, and obtained from an improved Forouhi-Bloomer parameterization model (FB-PM)

H. Van Cong

Université de Perpignan Via Domitia, Laboratoire de Mathématiques et Physique (LAMPS), EA 4217, Département de Physique, 52, Avenue Paul Alduy, F-66 860 Perpignan, France.

van-cong.huynh@univ-perp.fr ; huynhvc@outlook.fr

Abstract

In the n(p)-type degenerate InP-crystals, at low temperature T and high d(a)-density N , our expression for the static dielectric constant, $\epsilon(r_{d(a)})$, expressed as a function of the donor (acceptor) radius, $r_{d(a)}$, and determined by using an effective Bohr model, as that investigated in [1,2], suggests that, for an increasing $r_{d(a)}$, due to such the impurity size effect, $\epsilon(r_{d(a)})$ decreases, affecting strongly the critical d(a)-density in the metal-insulator transition (MIT), $N_{CDn(CDp)}(r_{d(a)})$, determined by Eq. (3), and its values are reported in Table 1, and also our accurate expressions for optical coefficients, obtained in Equations (24, 25, 28, 29), and their numerical results are given in Tables 2-6. Furthermore, one notes that, as observed in Table 3c, our obtained results of those optical coefficients are found to be more accurate than the corresponding ones, obtained from the FB-PM [11], suggesting thus that our present model, used here to study the optical properties of the n(p)-type degenerate InP-crystals, is a good improved FB-PM, as observed in Table 3c.

Keywords: Effects of the impurity-size and heavy doping; effective autocorrelation function for potential fluctuations; optical coefficients; critical photon energy

1. Introduction

Our new expression for the extrinsic static dielectric constant, $\epsilon(r_{d(a)})$, $r_{d(a)}$ being the donor (acceptor) $d(a)$ -radius, was determined by using an effective Bohr model, suggesting that, with an increasing $r_{d(a)}$, due thus to such the impurity size effect, $\epsilon(r_{d(a)})$ decreases, affecting strongly: the critical impurity density in the metal-insulator transition [1], figure of merit ZT [2], and also optical properties given in degenerate semiconductors [3].

In the following Sections 2-5 [4, 11], in the $n(p)$ -type degenerate InP-crystals, our numerical results of the optical coefficients, due to such the impurity-size effect, and obtained from an improved Forouhi-Bloomer parameterization model (**FB-PM**), are presented, and also compared with the corresponding experimental-and-theoretical ones [9, 11], suggesting that our present model is found to be a good improved FB-PM, as that observed in Table 3c. Finally, some concluding remarks are discussed and reported in Section 6.

2. Energy-band-structure parameters

First of all, in the following Table 1, we present the values of the energy-band-structure parameters, given in the $n(p)$ -type InP -crystal, such as: (i) if denoting the free electron mass by m_0 , the effective electron (hole) mass, $m_{n(p)}^*/m_0$, which is respectively equal to the relative effective mass, $m_{n(p)}/m_0 = 0.073$ (0.339) [2], as used in this Sections 2 and 4 to determine the critical impurity density in the metal-insulator transition (**MIT**), and (ii) to the reduced effective mas, $m_r/m_0 = \frac{m_n \times m_p}{m_n + m_p} = 0.060$, as used in Sections 3 and 5 to determine the optical band gap and the optical coefficients given in the $n(p)$ -type degenerate InP-crystal. Further, $E_{go} = E_{goP(goIn)} = 1.424$ eV [2] is the unperturbed intrinsic band gap, $\epsilon_0 = \epsilon_{P(In)} = 12.5$ is the relative static intrinsic dielectric constant of the InP-crystal, and finally, the effective averaged numbers of equivalent conduction (valence)-band edge, $g_{c(v)} = 1(1)$.

Table 1. For increasing $r_{d(a)}$, while $\epsilon(r_d)$ decreases, the functions: $E_{gni(gpi)}(r_{d(a)})$, $N_{CDn(NDp)}(r_{d(a)})$ and $N_{CDn(CDp)}^{EBT}(r_{d(a)})$ increase. The relative deviations between the numerical results of $N_{CDn}(r_d)$ and $N_{CDn}^{EBT}(r_d)$, calculated using Equations (3, 21), are very small, of the order of 7.61×10^{-4} , suggesting that $N_{CDn(NDp)}(r_{d(a)})$ can be well explained by $N_{CDn}^{EBT}(r_d)$, being localized in the EBT.

Donor		P	As	Te	Sb	Sn
r_d (nm) [4]	↗	0.110	0.118	0.132	0.136	0.140
$\epsilon(r_d)$	↘	12.5	12.20	10.57	9.987	9.40
$E_{gni}(r_d)$ in meV	↗	1424	1424.3	1426	1428	1429
$N_{CDn}(r_d)$ in 10^{16} cm^{-3}	↗	2.09	2.25	3.456	4.10	4.91
$N_{CDn}^{EBT}(r_d)$ in 10^{16} cm^{-3}	↗	2.09	2.24882	3.45636	4.0988	4.91274
$ RD $ in 10^{-4}		0	5.24	1.05	2.89	5.57
$\frac{k_{Fn}^{-1}}{k_{sn}^{-1}} < 1$ (Physical condition)		0.4012	0.4012	0.4012	0.4012	0.4012

Acceptor		Ga(Al)	Mg	In
r_a (nm) [4]	↗	0.126	0.140	0.144
$\epsilon(r_a)$	↘	13.418	12.543	12.5
$E_{gpi}(r_a)$ in meV	↗	1420	1423.8	1424
$N_{CDp}(r_a)$ in 10^{18} cm^{-3}	↗	1.692	2.072	2.090
$N_{CDp}^{EBT}(r_a)$ in 10^{18} cm^{-3}	↗	1.692	2.0713	2.0916
$ RD $ in 10^{-4}		0	3.45	7.61
$\frac{k_{fp}^{-1}}{k_{sp}^{-1}} < 1$ (Physical condition)		0.3364	0.3364	0.3363

We now determine our expression for extrinsic static dielectric constant, $\epsilon(r_{d(a)})$, due to the impurity size effect, and the expression for critical density, $N_{CDn(CDp)}(r_{d(a)})$, characteristic of the MIT, as follows.

2.1. Expression for $\epsilon(r_{d(a)})$

In the [d(a)-semiconductors]-systems, since $r_{d(a)}$, given in tetrahedral covalent bonds, is usually either larger or smaller than $r_{do(ao)} \equiv r_{p(In)}$, a local mechanical strain (or deformation potential energy) is induced, according to a compression (dilation) for: $r_{d(a)} > r_{do(ao)}$ ($r_{d(a)} < r_{do(ao)}$), due to the d(a)-size effect, respectively [1, 2]. Then, we have shown that this $r_{d(a)}$ -effect affects the changes in all the energy-band-structure parameters, expressed in terms of the static dielectric constant, $\epsilon(r_{d(a)})$, determined as follows.

At $T=0K$, we have showed [1, 2] that such the compression (dilatation) corresponds to the repulsive (attractive) force increases (decreases) the intrinsic energy gap $E_{gni(gpi)}(r_{d(a)})$ and the effective donor(acceptor)-ionization energy $E_{d(a)}(r_{d(a)})$ in absolute values, obtained in an effective Bohr model, as:

$$E_{gni(gpi)}(r_{d(a)}) - E_{go}(r_{do(ao)}) = E_{d(a)}(r_{d(a)}) - E_{do(ao)}(r_{do(ao)}) = E_{do(ao)}(r_{do(ao)}) \times \left[\left(\frac{\epsilon_0}{\epsilon(r_{d(a)})} \right)^2 - 1 \right], \quad (1)$$

where $E_{do(ao)}(r_{do(ao)}) \equiv \frac{13600 \text{ meV} \times (m_n(p)/m_0)}{\epsilon_0^2}$ and

$$\epsilon(r_{d(a)}) = \frac{\epsilon_0}{\sqrt{1 + \left[\left(\frac{r_{d(a)}}{r_{do(ao)}} \right)^3 - 1 \right] \times \ln \left(\frac{r_{d(a)}}{r_{do(ao)}} \right)^3}} \leq \epsilon_0, \text{ for } r_{d(a)} \geq r_{do(ao)},$$

$$\epsilon(r_{d(a)}) = \frac{\epsilon_0}{\sqrt{1 - \left[\left(\frac{r_{d(a)}}{r_{do(ao)}} \right)^3 - 1 \right] \times \ln \left(\frac{r_{d(a)}}{r_{do(ao)}} \right)^3}} \geq \epsilon_0, \left[\left(\frac{r_{d(a)}}{r_{do(ao)}} \right)^3 - 1 \right] \times \ln \left(\frac{r_{d(a)}}{r_{do(ao)}} \right)^3 < 1,$$

for 0.07014 nm (0.09182 nm) $< r_{d(a)} \leq r_{do(ao)}$, respectively. (2)

One notes that $\epsilon(r_{d(a)})$ decreases with an increasing $r_{d(a)}$, as observed in the above Table 1. In particular, in the B-InP system, in which $r_B = 0.088 \text{ nm} \ll r_{In} = 0.14 \text{ nm}$, the condition, given in Eq. (2), is found to be not satisfactory, since $\left[\left(\frac{r_B}{r_{In}} \right)^3 - 1 \right] \times \ln \left(\frac{r_B}{r_{In}} \right)^3 = 1.1402 > 1$. Therefore, as observed in Table 1, the B-InP system is absent.

2.2. Our expressions for the critical density in the MIT

In the n(p)-type degenerate InP-crystals, the critical donor(acceptor)-density, $N_{\text{CDn(NDp)}}(r_{\text{d(a)}})$, is determined from the generalized effective Mott criterion in the MIT, as:

$$N_{\text{CDn(NDp)}}(r_{\text{d(a)}})^{1/3} \times a_{\text{Bn(Bp)}}(r_{\text{d(a)}}) = 0.25, \quad (3)$$

and the effective Bohr radius $a_{\text{Bn(Bp)}}(r_{\text{d(a)}})$ is given by:

$$a_{\text{Bn(Bp)}}(r_{\text{d(a)}}) \equiv \frac{\varepsilon(r_{\text{d(a)}}) \times \hbar^2}{m_{\text{n(p)}}^* \times q^2} = 0.53 \times 10^{-8} \text{ cm} \times \frac{\varepsilon(r_{\text{d(a)}})}{(m_{\text{n(p)}}^*/m_0)}, \quad (4)$$

where $-q$ is the electron charge, $\varepsilon(r_{\text{d(a)}})$ is determined in Eq. (2), and $m_{\text{n(p)}}^*/m_0 = m_{\text{n(p)}}/m_0 = 0.073$ (0.339). From Eq. (3), the numerical results of $N_{\text{CDn(NDp)}}(r_{\text{d(a)}})$ are obtained and given in the above Table 1, in which we also report those of the densities of electrons (holes) localized in exponential conduction (valance)-band (EBT) tails, $N_{\text{CDn(CDp)}}^{\text{EBT}}(r_{\text{d(a)}})$, obtained using Eq. (21), as investigated in Section 4, noting that the maximal relative deviations (RD), in absolute values, between $N_{\text{CDn(NDp)}}(r_{\text{d(a)}})$ and $N_{\text{CDn(CDp)}}^{\text{EBT}}(r_{\text{d(a)}})$ are found to be equal to: $5.57(7.61) \times 10^{-4}$, respectively. Thus, $N_{\text{CDn(NDp)}}(r_{\text{d(a)}})$ determined in Eq. (3), can be explained by the densities of electrons (holes) localized in exponential conduction (valance)-band (EBT) tails, $N_{\text{CDn(CDp)}}^{\text{EBT}}(r_{\text{d(a)}})$, determined in Eq. (21).

Furthermore, in our recent work [7], we also showed that, in n(p)-type degenerate InP-crystals, the critical densities of electrons (holes) can also be determined from the spin-susceptibility singularities (SSS), obtained at $N = N_{\text{CDn(CDp)}}^{\text{SSS}}(r_{\text{d(a)}})$, at which the metal-insulator transition (MIT) occurs.

In summary, Table 1 also indicates that, for an increasing $r_{\text{d(a)}}$, $\varepsilon(r_{\text{d(a)}})$ decreases, while $\mathbb{E}_{\text{gni(gpi)}}(r_{\text{d(a)}})$, $N_{\text{CDn(NDp)}}(r_{\text{d(a)}})$ and $N_{\text{CDn(CDp)}}^{\text{EBT}}(r_{\text{d(a)}})$ increase, affecting strongly all the physical properties, as those observed in following Sections 3-5.

3. Optical band gap

Here, $m_{\text{n(p)}}^*/m_0$ is chosen as: $m_{\text{n(p)}}^*/m_0 = m_{\text{r}}/m_0 = 0.060$, and then, if denoting $N^* \equiv N - N_{\text{CDn(NDp)}}(r_{\text{d(a)}})$, the optical band gap (**OBG**) is found to be given by:

$$\mathbb{E}_{\text{gn1(gp1)}}(N^*, r_{\text{d(a)}}, T) \equiv \mathbb{E}_{\text{gn2(gp2)}}(N^*, r_{\text{d(a)}}, T) + \mathbb{E}_{\text{Fn(Fp)}}(N^*, T), \quad (5)$$

where the Fermi energy $\mathbb{E}_{\text{Fn(Fp)}}(N^*, T)$ is determined in Eq. (A3) of the Appendix A and the reduced band gap is defined by:

$$\mathbb{E}_{\text{gn2(gp2)}}(N^*, r_{\text{d(a)}}, T) \equiv \mathbb{E}_{\text{gnei(gpei)}}(r_{\text{d(a)}}, T) - \Delta \mathbb{E}_{\text{gn(gp)}}(N^*, r_{\text{d(a)}}).$$

Here, the effective intrinsic band gap $\mathbb{E}_{\text{gnei(gpei)}}(r_{\text{d(a)}})$ is determined by:

$$\mathbb{E}_{\text{gnei(gpei)}}(r_{\text{d(a)}}, T) \equiv \mathbb{E}_{\text{gni(gpi)}}(r_{\text{d(a)}}) - \frac{4.9 \times 10^{-4} \times T^2}{T + 327 \text{ K}},$$

and the band gap narrowing, $\Delta \mathbb{E}_{\text{gn(gp)}}(N^*, r_{\text{d(a)}})$, are determined in Equations (B3, B4) of the Appendix B and the values of $\mathbb{E}_{\text{gni(gpi)}}(r_{\text{d(a)}})$ are given in Table 1.

Then, as noted in the Appendix A and B, at $T=0K$, as $N^* = 0$, one has: $\mathbb{E}_{Fn(Fp)}(N^*, T) = \mathbb{E}_{Fno(Fpo)}(N^*) = 0$, as given in Eq. (A4), and $\Delta E_{gn(gp)}(N^*, r_{d(a)}) = 0$, according to the MIT, as noted in Appendix A and B. Therefore, $\mathbb{E}_{gn1(gp1)} = \mathbb{E}_{gn2(gp2)} = \mathbb{E}_{gnei(gpei)}(r_{d(a)}) = \mathbb{E}_{gni(gpi)}(r_{d(a)})$ at $T=0K$ and $N^* = 0$, according also to the MIT.

4. Physical model and mathematical methods

4.1. Physical model

In the n(p)-type degenerate InP, if denoting the Fermi wave number by: $k_{Fn(Fp)}(N) \equiv (3\pi^2 N/g_{c(v)})^{1/3}$, the effective reduced Wigner-Seitz radius $r_{sn(sp)}$, characteristic of the interactions, is defined by

$$\gamma \times r_{sn(sp)}(N^*, r_{d(a)}, m_{n(p)}^*) \equiv \frac{k_{Fn(Fp)}^{-1}}{a_{Bn(Bp)}} < 1, \quad (6)$$

being proportional to $N^{*-1/3}$. Here, $\gamma = (4/9\pi)^{1/3}$, $k_{Fn(Fp)}^{-1}$ means the averaged distance between ionized donors (acceptors), and $a_{Bn(Bp)}(r_{d(a)})$ is determined in Eq. (4).

Then, the ratio of the inverse effective screening length $k_{sn(sp)}$ to Fermi wave number $k_{Fn(kp)}$ at 0 K is defined by

$$R_{sn(sp)}(N^*, r_{d(a)}) \equiv \frac{k_{sn(sp)}}{k_{Fn(Fp)}} = \frac{k_{Fn(Fp)}^{-1}}{k_{sn(sp)}^{-1}} = R_{snWS(spWS)} + [R_{snTF(spTF)} - R_{snWS(spWS)}]e^{-r_{sn(sp)}} < 1. \quad (7)$$

These ratios, $R_{snTF(spTF)}$ and $R_{snWS(spWS)}$, can be determined as follows.

First, for $N \gg N_{CDn(NDp)}(r_{d(a)})$, according to the Thomas-Fermi (TF)-approximation, the ratio $R_{snTF(snTF)}$ is reduced to

$$R_{snTF}(N^*, r_{d(a)}) \equiv \frac{k_{snTF(spTF)}}{k_{Fn(Fp)}} = \frac{k_{Fn(Fp)}^{-1}}{k_{snTF(spTF)}^{-1}} = \sqrt{\frac{4\gamma r_{sn(sp)}}{\pi}} \ll 1, \quad (8)$$

being proportional to $N^{-1/6}$.

Secondly, for $N < N_{CDn(NDp)}(r_{d(a)})$, according to the Wigner-Seitz (WS)-approximation, the ratio $R_{snWS(snWS)}$ is respectively reduced to

$$R_{sn(sp)WS}(N^*, r_{d(a)}) \equiv \frac{k_{sn(sp)WS}}{k_{Fn}} = 0.5 (1) \times \left(\frac{3}{2\pi} - \gamma^d \frac{[r_{sn(sp)}^2 \times \mathbb{E}_{CE}(N^*, r_{d(a)})]}{dr_{sn(sp)}} \right), \quad (9)$$

where $\mathbb{E}_{CE}(N^*, r_{d(a)})$ is the majority-carrier correlation energy (CE), being determined in Eq. (B2) of the Appendix B.

Furthermore, as given in I, in the highly degenerate case, the physical conditions, as those observed in Table 1, are found to be given by :

$$\frac{k_{Fn(Fp)}^{-1}}{a_{Bn(Bp)}} < \frac{\eta_{n(p)}}{\mathbb{E}_{Fno(Fpo)}} \equiv \frac{1}{A_{n(p)}} < \frac{k_{Fn(Fp)}^{-1}}{k_{sn(sp)}^{-1}} \equiv R_{sn(sp)} < 1, \quad A_{n(p)} \equiv \frac{\mathbb{E}_{Fno(Fpo)}}{\eta_{n(p)}}, \quad (10)$$

being needed to determine the expression for electrical conductivity, as investigated in Section 5. Here, $R_{sn(sp)}$ is defined in Eq. (7).

Then, in degenerate d(a)-InP systems, the total screened Coulomb impurity potential energy due to the attractive interaction between an electron(hole) charge, $-q(+q)$, at position \vec{r} , and an ionized donor (ionized acceptor) charge: $+q(-q)$ at position \vec{R}_j , randomly distributed throughout the InP- crystal, is defined by

$$V(r) \equiv \sum_{j=1}^N v_j(r) + V_o, \quad (11)$$

where N is the total number of ionized donors(acceptors), V_o is a constant potential energy, and $v_j(r)$ is a screened Coulomb potential energy for each d(a)-InP system, defined as

$$v_j(r) \equiv -\frac{q^2 \times \exp(-k_{sn(sp)} \times |\vec{r} - \vec{R}_j|)}{\epsilon(r_{d(a)}) \times |\vec{r} - \vec{R}_j|},$$

where $k_{sn(sp)}$ is the inverse screening length determined in Eq. (7).

Further, using a Fourier transform, the v_j -representation in wave vector \vec{k} -space is given by

$$v_j(\vec{k}) = -\frac{q^2}{\epsilon(r_{d(a)})} \times \frac{4\pi}{\Omega} \times \frac{1}{k^2 + k_{sn}^2},$$

where Ω is the total InP -crystal volume.

Then, the effective auto-correlation function for potential fluctuations, $W_{n(p)}(v_{n(p)}, N^*, r_d) \equiv \langle V(r)V(r') \rangle$, was determined in II, as :

$$W_{n(p)}(v_{n(p)}, N^*, r_{d(a)}) \equiv \eta_{n(p)}^2 \times \exp\left(\frac{-\mathcal{H} \times R_{sn(sp)}(N^*, r_{d(a)})}{2\sqrt{|v_{n(p)}|}}\right), \quad \eta_{n(p)}(N^*, r_{d(a)}) \equiv \frac{\sqrt{2\pi N^*}}{\epsilon(r_{d(a)})} \times q^2 k_{sn(sp)}^{-1/2}, \quad v_{n(p)} \equiv \frac{-\mathbb{E}}{\mathbb{E}_{Fno(Fpo)}}. \quad (12)$$

Here, $\epsilon(r_{d(a)})$ is determined in Eq. (2), $R_{sn(sp)}(N^*, r_{d(a)})$ in Eq. (7), the empirical Heisenberg parameter $\mathcal{H} = 0.4721$ (1.585), respectively, will be chosen such that the determination of the density of electrons localized in the conduction(valence)-band tails, determined in Section 5 would be accurate, and finally $v_{n(p)} \equiv \frac{-\mathbb{E}}{\mathbb{E}_{Fno(Fpo)}}$, where \mathbb{E} is the total electron energy and $\mathbb{E}_{Fno(Fpo)}$ is the Fermi energy at 0 K, determined in Eq. (A4) of the Appendix A.

In the following, we will calculate the ensemble average of the function: $(\mathbb{E} - V)^{a-\frac{1}{2}} \equiv \mathbb{E}_k^{a-\frac{1}{2}}$, for $a \geq 1$,

$\mathbb{E}_k \equiv \frac{\hbar^2 \times k^2}{2 \times m_{n(p)}^*}$ being the kinetic energy of the electron (hole), and $V(r)$ determined in Eq. (11), by using the two following integration methods, as developed in II, which strongly depend on $W_{n(p)}(v_{n(p)}, N^*, r_{d(a)})$.

4.2. Mathematical methods and their application (Critical impurity density)

A. Kane integration method (KIM)

In heavily doped d(a)- InP systems, the effective Gaussian distribution probability is defined by

$$P(V) \equiv \frac{1}{\sqrt{2\pi W_{n(p)}}} \times \exp\left[\frac{-V^2}{2W_{n(p)}}\right].$$

So, in the Kane integration method, the Gaussian average of $(\mathbb{E} - V)^{a-\frac{1}{2}} \equiv \mathbb{E}_k^{a-\frac{1}{2}}$ is defined by

$$\langle (\mathbb{E} - V)^{a-\frac{1}{2}} \rangle_{KIM} \equiv \langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{KIM} = \int_{-\infty}^{\mathbb{E}} (\mathbb{E} - V)^{a-\frac{1}{2}} \times P(V) dV, \quad \text{for } a \geq 1.$$

Then, by variable changes: $s = (\mathbb{E} - V)/\sqrt{W_{n(p)}}$ and $x = -\mathbb{E}/\sqrt{W_{n(p)}} \equiv A_{n(p)} \times v_{n(p)} \times \exp\left(\frac{\mathcal{H} \times R_{sn(sp)}}{4 \times \sqrt{|v_{n(p)}|}}\right)$,

and using an identity:

$$\int_0^\infty s^{a-\frac{1}{2}} \times \exp\left(-xs - \frac{s^2}{2}\right) ds \equiv \Gamma\left(a + \frac{1}{2}\right) \times \exp(x^2/4) \times D_{-a-\frac{1}{2}}(x),$$

where $D_{-a-\frac{1}{2}}(x)$ is the parabolic cylinder function and $\Gamma(a + \frac{1}{2})$ is the Gamma function, one thus has:

$$\langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{\text{KIM}} = \frac{\exp(-x^2/4) \times W_{n(p)}^{\frac{2a-1}{4}}}{\sqrt{2\pi}} \times \Gamma\left(a + \frac{1}{2}\right) \times D_{-a-\frac{1}{2}}(x) = \frac{\exp(-x^2/4) \times \eta_{n(p)}^{a-\frac{1}{2}}}{\sqrt{2\pi}} \times \exp\left(-\frac{\mathcal{H} \times R_{sn(sp)} \times (2a-1)}{8 \times \sqrt{|v_{n(p)}|}}\right) \times \Gamma\left(a + \frac{1}{2}\right) \times D_{-a-\frac{1}{2}}(x). \quad (13)$$

B. Feynman path-integral method (FPIM)

Here, the ensemble average of $(\mathbb{E} - V)^{a-\frac{1}{2}} \equiv \mathbb{E}_k^{a-\frac{1}{2}}$ is defined by

$$\langle (\mathbb{E} - V)^{a-\frac{1}{2}} \rangle_{\text{FPIM}} \equiv \langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{\text{FPIM}} \equiv \frac{\hbar^{a-\frac{1}{2}}}{2^{3/2} \times \sqrt{2\pi}} \times \frac{\Gamma(a+\frac{1}{2})}{\Gamma(\frac{3}{2})} \times \int_{-\infty}^{\infty} (it)^{-a-\frac{1}{2}} \times \exp\left\{\frac{iEt}{\hbar} - \frac{(t\sqrt{W_{n(p)}})^2}{2\hbar^2}\right\} dt, \quad i^2 = -1,$$

noting that as $a=1$, $(it)^{-\frac{3}{2}} \times \exp\left\{-\frac{(t\sqrt{W_{n(p)}})^2}{2\hbar^2}\right\}$ is found to be proportional to the averaged Feynman propagator given the dense donors(acceptors).

Then, by variable changes: $t = \frac{\hbar}{\sqrt{W_{n(p)}}}$ and $x = -\mathbb{E}/\sqrt{W_{n(p)}}$, and then using an identity:

$$\int_{-\infty}^{\infty} (is)^{-a-\frac{1}{2}} \times \exp\left\{ixs - \frac{s^2}{2}\right\} ds \equiv 2^{3/2} \times \Gamma(3/2) \times \exp(-x^2/4) \times D_{-a-\frac{1}{2}}(x),$$

one finally obtains: $\langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{\text{FPIM}} \equiv \langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{\text{KIM}}$, $\langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{\text{KIM}}$ being determined in Eq. (13).

In the following, with use of asymptotic forms for $D_{-a-\frac{1}{2}}(x)$, those given for $\langle (\mathbb{E} - V)^{a-\frac{1}{2}} \rangle_{\text{KIM}}$ will be obtained in the two cases: $\mathbb{E} \geq 0$ and $\mathbb{E} \leq 0$.

(i) $\mathbb{E} \geq 0$ -case

As $\mathbb{E} \rightarrow +\infty$, one has: $v_n \rightarrow -\infty$ and $x \rightarrow -\infty$. In this case, one gets:

$$D_{-a-\frac{1}{2}}(x \rightarrow -\infty) \approx \frac{\sqrt{2\pi}}{\Gamma(a+\frac{1}{2})} \times e^{\frac{x^2}{4}} \times (-x)^{a-\frac{1}{2}}.$$

Therefore, Eq. (13) becomes: $\langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{\text{KIM}} \approx \mathbb{E}^{a-\frac{1}{2}}$. Further, as $\mathbb{E} \rightarrow +0$, one has: $v_{n(p)} \rightarrow -0$ and $x \rightarrow -\infty$. So, one gets :

$$D_{-a-\frac{1}{2}}(x \rightarrow -\infty) \simeq \beta(a) \times \exp\left(\left(\sqrt{a} + \frac{1}{3}\right)x - \frac{x^2}{16a} + \frac{x^3}{24\sqrt{a}}\right) \rightarrow 0, \quad \beta(a) = \frac{\sqrt{\pi}}{2^{\frac{2a+1}{4}} \Gamma(\frac{a}{2} + \frac{3}{4})}.$$

Thus, as $\mathbb{E} \rightarrow +0$, from Eq. (13), one gets: $\langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{\text{KIM}} \rightarrow 0$.

In summary, for $\mathbb{E} \geq 0$, the expression of $\langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{\text{KIM}}$ can be approximated by:

$$\langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{\text{KIM}} \cong \mathbb{E}^{a-\frac{1}{2}}, \quad \mathbb{E}_k \equiv \frac{\hbar^2 \times k^2}{2 \times m^*}. \quad (14)$$

(ii) $\mathbb{E} \leq 0$ – case.

As $\mathbb{E} \rightarrow -0$, from Eq. (13), one has: $v_{n(p)} \rightarrow +0$ and $x \rightarrow +\infty$. Thus, one first obtains, for any $a \geq 1$,

$$D_{-a-\frac{1}{2}}(x \rightarrow \infty) \simeq \beta(a) \times \exp \left[-(\sqrt{a} + \frac{1}{3})x - \frac{x^2}{16a} - \frac{x^3}{24\sqrt{a}} \right] \rightarrow 0, \quad \beta(a) = \frac{\sqrt{\pi}}{2^{\frac{2a+1}{4}} \Gamma(\frac{a+3}{4})}, \text{ noting that}$$

$$\beta(1) = \frac{\sqrt{\pi}}{2^{\frac{3}{4}} \Gamma(5/4)} \text{ and } \beta(5/2) = \frac{\sqrt{\pi}}{2^{3/2}}.$$

Then, putting $f(a) \equiv \frac{\eta_{n(p)}^{a-\frac{1}{2}}}{\sqrt{2\pi}} \times \Gamma(a + \frac{1}{2}) \times \beta(a)$, Eq. (13) yields

$$H_{n(p)}(v_{n(p)} \rightarrow +0, r_{d(a)}, a) = \frac{\langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{\text{KIM}}}{f(a)} = \exp \left[-\frac{\mathcal{H} \times R_{\text{sn(sp)}} \times (2a-1)}{8 \times \sqrt{|v_{n(p)}|}} - \left(\sqrt{a} + \frac{1}{3} \right) x - \frac{(\frac{1}{4} + \frac{1}{16a})x^2 - \frac{x^3}{24\sqrt{a}}}{16a^2} \right] \rightarrow 0. \quad (15)$$

Further, as $\mathbb{E} \rightarrow -\infty$, one has: $v_{n(p)} \rightarrow +\infty$ and $x \rightarrow \infty$. Thus, one gets:

$$D_{-a-\frac{1}{2}}(x \rightarrow \infty) \approx x^{-a-\frac{1}{2}} \times e^{-\frac{x^2}{4}} \rightarrow 0. \text{ Therefore, Eq. (13) yields}$$

$$K_{n(p)}(v_{n(p)} \rightarrow +\infty, r_{d(a)}, a) \equiv \frac{\langle \mathbb{E}_k^{a-\frac{1}{2}} \rangle_{\text{KIM}}}{f(a)} \simeq \frac{1}{\beta(a)} \times \exp \left(-\frac{(A_{n(p)} \times v_{n(p)})^2}{2} \right) \times (A_{n(p)} \times v_{n(p)})^{-a-\frac{1}{2}} \rightarrow 0. \quad (16)$$

It should be noted that, as $\mathbb{E} \leq 0$, the ratios (15) and (16) can be taken in an approximate form as:

$$F_{n(p)}(v_{n(p)}, r_{d(a)}, a) = K_{n(p)}(v_{n(p)}, r_{d(a)}, a) + [H_{n(p)}(v_{n(p)}, r_{d(a)}, a) - K_{n(p)}(v_{n(p)}, r_{d(a)}, a)] \times \exp [-c_1 \times (A_{n(p)} v_{n(p)})^{c_2}], \quad (17)$$

such that: $F_{n(p)}(v_{n(p)}, r_{d(a)}, a) \rightarrow H_{n(p)}(v_{n(p)}, r_{d(a)}, a)$ for $0 \leq v_n \leq 16$, and $F_{n(p)}(v_{n(p)}, r_{d(a)}, a) \rightarrow K_{n(p)}(v_{n(p)}, r_{d(a)}, a)$ for $v_{n(p)} \geq 16$. Here, the constants c_1 and c_2 may be respectively chosen as: $c_1 = 10^{-40}$ and $c_2 = 80$, as $a = 1$, being used to determine the critical density of electrons (holes) localized in the exponential conduction(valence) band-tails (EBT), $N_{\text{CDn(CDp)}}^{\text{EBT}}(N, r_{d(a)})$, in the following.

C. Critical impurity density in the MIT

In degenerate d(a)- InP systems at $T=0$ K, in which $m_{n(p)}^*/m_0 = m_{n(p)}/m_0 = 0.073(0.339)$, as given in Section 2, using Eq. (13), for $a=1$, the density of states $\mathcal{D}(\mathbb{E})$ is defined by:

$$\langle \mathcal{D}(\mathbb{E}_k) \rangle_{\text{KIM}} \equiv \frac{g_c(v)}{2\pi^2} \left(\frac{2m_{n(p)}}{\hbar^2} \right)^{\frac{3}{2}} \times \langle \mathbb{E}_k^{\frac{1}{2}} \rangle_{\text{KIM}} = \frac{g_c(v)}{2\pi^2} \left(\frac{2m_{n(p)}}{\hbar^2} \right)^{\frac{3}{2}} \times \frac{\exp \left(-\frac{x^2}{4} \right) \times W_n^{\frac{1}{4}}}{\sqrt{2\pi}} \times \Gamma\left(\frac{3}{2}\right) \times D_{-\frac{3}{2}}(x) = \mathcal{D}(\mathbb{E}), \quad (18)$$

where x is defined in Eq. (13), as: $x = -\mathbb{E}/\sqrt{W_{n(p)}} \equiv A_{n(p)} \times v_{n(p)} \times \exp \left(\frac{\mathcal{H} \times R_{\text{sn(sp)}}}{4 \times \sqrt{|v_{n(p)}|}} \right)$.

Here, \mathbb{E}_{Fno} is determined in Eq. (A4) of the Appendix A, with $m_{n(p)}^*/m_0 = m_{n(p)}/m_0$ and $\mathcal{H} = 0.4721(1.585)$, respectively, being chosen such that the following determination of $N_{\text{CDn(CDp)}}^{\text{EBT}}(N, r_{d(a)})$ would be accurate.

Going back to the functions: H_n , K_n and F_n , given respectively in Equations (15-17), in which the factor

$\frac{1}{f(a=1)} \langle \mathbb{E}_k^2 \rangle_{KIM}$ is now replaced by:

$$\frac{1}{f(a=1)} \langle \mathbb{E}_k^2 \rangle_{KIM} = \frac{\mathcal{D}(\mathbb{E} \leq 0)}{\mathcal{D}_0} = F_{n(p)}(v_{n(p)}, r_{d(a)}, a = 1), \mathcal{D}_0 = \frac{g_{c(v)} \times (m_{n(p)} \times m_o)^{3/2} \times \sqrt{\eta_{n(p)}}}{2\pi^2 \hbar^3} \times \beta(a = 1), \beta(a = 1) = \frac{\sqrt{\pi}}{2^4 \times \Gamma(5/4)}. \quad (19)$$

Therefore, $N_{CDn(CDp)}^{EBT}(N, r_{d(a)})$ can be defined by

$$N_{CDn(CDp)}^{EBT}(N, r_{d(a)}) = \int_{-\infty}^0 \mathcal{D}(\mathbb{E} \leq 0) d\mathbb{E},$$

where $\mathcal{D}(\mathbb{E} \leq 0)$ is determined in Eq. (19). Then, by a variable change: $v_{n(p)} \equiv \frac{-\mathbb{E}}{\mathbb{E}_{Fno(Fpo)}}$, one obtains:

$$N_{CDn(CDp)}^{EBT}(N, r_{d(a)}) = \frac{g_{c(v)} \times (m_{n(p)})^{3/2} \sqrt{\eta_{n(p)}} \times \mathbb{E}_{Fno(Fpo)}}{2\pi^2 \hbar^3} \times \left\{ \int_0^{16} \beta(a = 1) \times F_{n(p)}(v_{n(p)}, r_{d(a)}, a = 1) dv_{n(p)} + I_{n(p)} \right\}, \quad (20)$$

where

$$I_{n(p)} \equiv \int_{16}^{\infty} \beta(a = 1) \times K_{n(p)}(v_{n(p)}, r_{d(a)}, a = 1) dv_{n(p)} = \int_{16}^{\infty} e^{\frac{-(A_{n(p)} \times v_{n(p)})^2}{2}} \times (A_{n(p)} v_{n(p)})^{-3/2} dv_{n(p)}.$$

$$\text{Here, } \beta(a = 1) = \frac{\sqrt{\pi}}{2^4 \times \Gamma(5/4)}.$$

Then, by another variable change: $t = [A_{n(p)} v_{n(p)} / \sqrt{2}]^2$, the integral $I_{n(p)}$ yields:

$$I_{n(p)} = \frac{1}{2^{5/4} A_{n(p)}} \times \int_{y_{n(p)}}^{\infty} t^{b-1} e^{-t} dt \equiv \frac{\Gamma(b, y_{n(p)})}{2^{5/4} \times A_{n(p)}},$$

where $b = -1/4$, $y_{n(p)} = [16 A_{n(p)} / \sqrt{2}]^2$, and $\Gamma(b, y_{n(p)})$ is the incomplete Gamma function, defined by:

$$\Gamma(b, y_{n(p)}) \simeq y_{n(p)}^{b-1} \times e^{-y_{n(p)}} \left[1 + \sum_{j=1}^{16} \frac{(b-1)(b-2)\dots(b-j)}{y_{n(p)}^j} \right].$$

Finally, Eq. (20) now yields:

$$N_{CDn(CDp)}^{EBT}[N = N_{CDn(NDp)}(r_{d(a)}), r_{d(a)}] = \frac{g_{c(v)} \times (m_{n(p)})^{3/2} \sqrt{\eta_{n(p)}} \times \mathbb{E}_{Fno(Fpo)}}{2\pi^2 \hbar^3} \times \left\{ \int_0^{16} \beta(a = 1) \times F_{n(p)}(v_{n(p)}, r_{d(a)}, a = 1) dv_{n(p)} + \frac{\Gamma(b, y_{n(p)})}{2^{5/4} \times A_{n(p)}} \right\}, \quad (21)$$

being the density of electrons(holes) localized in the exponential conduction(valence)-band tails (EBT), respectively.

The numerical results of $N_{CDn(CDp)}^{EBT}[N = N_{CDn(NDp)}(r_{d(a)}), r_{d(a)}] \equiv N_{CDn(CDp)}^{EBT}(r_{d(a)})$, for a simplicity of presentation, evaluated using Eq. (21), are given in Table 1, confirming thus those of $N_{CDn(NDp)}(r_{d(a)})$, calculated using Eq. (3), with a precision of the order of $5.57(7.61) \times 10^{-4}$, respectively. In other word, this critical $d(a)$ -density $N_{CDn(NDp)}(r_{d(a)})$ can thus be explained by the density of electrons(holes) localized in the EBT, $N_{CDn(CDp)}^{EBT}(r_{d(a)})$, respectively.

So, the effective density of free electrons (holes), N^* , given in the parabolic conduction (valence) band of the degenerate d(a)- InP systems, can thus be expressed by:

$$N^* \equiv N - N_{\text{CDn(NDp)}} \cong N - N_{\text{CDn(CDp)}}^{\text{EBT}}. \quad (22)$$

Then, if $N^* = N_{\text{CDn(NDp)}}$, according to the Fermi energy, $E_{\text{Fn0(Fp0)}}(N^* = N_{\text{CDn(NDp)}}) \equiv \frac{\hbar^2 \times k_{\text{Fn(Fp)}}^2(N^*)}{2 \times m_{\text{n(p)}}^*}$, then the value of the density of electrons(holes), $N_{\text{CDn(CDp)}}^{\text{EBT}}$, localized in the EBT for $E \leq 0$, is almost equal to $N_{\text{CDn(NDp)}}$, given in this parabolic conduction (valence) band, for $E \geq 0$. This can thus be expressed as:

$$N_{\text{CDn(CDp)}}^{\text{EBT}} \cong N_{\text{CDn(NDp)}}, \text{ as } N^* \equiv N_{\text{CDn(NDp)}}. \quad (23)$$

5. Optical coefficients

Here, $m_{\text{n(p)}}^*/m_0$ is chosen as: $m_{\text{n(p)}}^*/m_0 = m_r/m_0 = 0.060$, as that used in Section 3, for determining the optical band gap in degenerate GaAs-crystals.

The optical properties of any medium can be described by the complex refraction index \mathbb{N} and the complex dielectric function ε , $\mathbb{N} \equiv n - i\kappa$ and $\varepsilon \equiv \varepsilon_1 - i\varepsilon_2$, where $i^2 = -1$ and $\varepsilon \equiv \mathbb{N}^2$. Therefore, the real and imaginary parts of ε denoted by ε_1 and ε_2 can thus be expressed in terms of the refraction index n and the extinction coefficient κ as: $\varepsilon_1 \equiv n^2 - \kappa^2$ and $\varepsilon_2 \equiv 2n\kappa$. One notes that the optical absorption coefficient α is related to ε_2 , n , κ , and the optical conductivity σ_0 by [3]

$$\alpha(E) \equiv \frac{\hbar q^2 \times |v(E)|^2}{n(E) \times \varepsilon_{\text{free space}} \times c E} \times J(E^*) = \frac{E \times \varepsilon_2(E)}{\hbar c n(E)} \equiv \frac{2E \times \kappa(E)}{\hbar c} \equiv \frac{4\pi\sigma_0(E)}{c n(E) \times \varepsilon_{\text{free space}}}, \quad \varepsilon_1 \equiv n^2 - \kappa^2 \text{ and } \varepsilon_2 \equiv 2n\kappa, \quad (24)$$

where the effective photon energy: $E^* = E - E_{\text{gn(gp)}} = E$ is the reduced photon energy, the band gap $E_{\text{gn(gp)}}$ can be equal to the optical band gap $E_{\text{gn1(gp1)}}$ and intrinsic band gap $E_{\text{gni(gpi)}}$, determined in Eq. (5). Here, $E \equiv \hbar\omega$, $-q$, \hbar , $|v(E)|$, ω , $\varepsilon_{\text{free space}}$, c and $J(E^*)$ respectively represent: the photon energy, electron charge, Dirac's constant, matrix elements of the velocity operator between valence (conduction)-and-conduction (valence) bands in n(p)-type semiconductors, photon frequency, permittivity of free space, velocity of light, and joint density of states. It should be noted that, if the three functions such as: $|v(E)|^2$, $J(E^*)$ and $n(E)$ are known, then the other optical dispersion functions given in Eq. (24) can thus be determined. Moreover, the normal-incidence reflectance, $R(E)$, can be expressed in terms of $\kappa(E)$ and $n(E)$ as:

$$R(E) = \frac{[n(E)-1]^2 + \kappa(E)^2}{[n(E)+1]^2 + \kappa(E)^2} \quad (25)$$

From Equations (24, 25), if the two optical functions, ε_1 and ε_2 , (or n and κ), are both known, the other ones defined above can thus be determined.

Then, using a transformation for the joint density of states, given in allowed direct InP -transitions, at low values of E , $E_{\text{gni(gpi)}} \leq E \leq E_o = 2.5 \text{ eV}$,

$$J_{\text{n(p)}}(E) = \frac{1}{2\pi^2} \times \left(\frac{2m_r}{\hbar^2}\right)^{3/2} \times E_{\text{gni(gpi)}}^{1-a} \times (E - E_{\text{gn(gp)}})^{a-(1/2)} = \frac{1}{2\pi^2} \times \left(\frac{2m_r}{\hbar^2}\right)^{3/2} \times E_{\text{gni(gpi)}}^{13/30} \times (E - E_{\text{gn(gp)}})^{1/15}, \quad \text{for } a=17/30, \quad (26)$$

and at large values of E , $E \geq E_o = 2.5 \text{ eV}$,

$$J_{n(p)}(E) = \frac{1}{2\pi^2} \times \left(\frac{2m_r}{\hbar^2}\right)^{3/2} \times \frac{(E - E_{gn(gp)})^{a-(1/2)}}{E_{gni(gpi)}^{a-1}} = \frac{1}{2\pi^2} \times \left(\frac{2m_r}{\hbar^2}\right)^{3/2} \times \frac{(E - E_{gn(gp)})^2}{E_{gni(gpi)}^{3/2}}, \text{ for } a=5/2. \quad (27)$$

Further, one notes that, as $E \rightarrow \infty$, Forouhi and Bloomer (FB) [11] claimed that $\kappa(E \rightarrow \infty) \rightarrow$ a constant, while the $\kappa(E)$ -expressions, proposed by Jellison and Modine [12] and by Van Cong [3] quickly go to 0 as E^{-3} , and consequently, their numerical results of the optical functions such as: $\sigma_0(E)$ and $\alpha(E)$, given in Eq. (24), both go 0 as E^{-2} .

Now, taking into account Equations (26, 27) and also above remarks, an improved Forouhi-Bloomer parameterization model (FB-PM), used to determine the accurate expressions of the optical coefficients, obtained in the degenerate n(p) type InP-crystals, is proposed as follows.

If defining the band gap $E_{gn(gp)}$, which can be equal to the optical band gap $E_{gn1(gp1)}$, the effective intrinsic band gap $E_{gnei(gpei)}$, or to the intrinsic band gap $E_{gni(gpi)}$, and $f(E) \equiv \sum_{i=1}^4 \frac{A_i}{E^2 \times (1 + 10^{-4} \times \frac{E}{E_g}) - B_i E + C_i}$, we propose:

$$\begin{aligned} \kappa(E^*) &= f(E) \times E_{gni(gpi)}^{29/15} \times (E^* \equiv E - E_{gn1(gp1)})^{1/15}, \text{ for } E_{gni(gpi)} \leq E \leq 2.5 \text{ eV}, \\ &= f(E) \times (E^* \equiv E - E_{gn1(gp1)})^2, \text{ for } E \geq 2.5 \text{ eV}, \end{aligned} \quad (28)$$

being equal to 0 for $E^* = 0$ (or for $E = E_{gn1(gp1)}$), and also going to 0 as E^{-1} as $E \rightarrow \infty$, and further,

$$n(E) = n_{\infty}(r_{d(a)}) + \sum_{i=1}^4 \frac{B_{oi}E + C_{oi}}{E^2 - B_i E + C_i}, \quad (29)$$

going to a constant as $E \rightarrow \infty$, since $n(E \rightarrow \infty, r_{d(a)}) = n_{\infty}(r_{d(a)}) = \sqrt{\epsilon(r_{d(a)})} \times \frac{\omega_T}{\omega_L}$, $\omega_T = 5.3 \times 10^{13} \text{ s}^{-1}$

[5] and $\omega_L = 1.1023 \times 10^{14} \text{ s}^{-1}$, according to $n_{\infty}(r_p) = 1.6999$, obtained from the Lyddane-Sachs-Teller relation [5], from which T(L) represents the transverse (longitudinal) optical phonon mode, while in the FB-PM [11], $n_{\infty}(\text{FB}) = 1.766$ and the band gap $E_g = 1.27 \text{ eV} < E_{gni(gpi)}$, for the InP-crystal, as observed in

Table 1. Here, other parameters are determined by [11]: $B_{oi} = \frac{A_i}{Q_i} \times \left[-\frac{B_i^2}{2} + E_{gnei(gpei)} B_i - E_{gnei(gpei)}^2 + C_i \right]$,

$$C_{oi} = \frac{A_i}{Q_i} \times \left[\frac{B_i \times (E_{gnei(gpei)}^2 + C_i)}{2} - 2E_{gnei(gpei)} C_i \right], \quad Q_i = \frac{\sqrt{4C_i - B_i^2}}{2}, \text{ where, for } i=(1, 2, 3, \text{ and } 4), A_i = 1.18 \times A_{i(\text{FB})} = 0.2389, 0.0276, 0.0363, 0.052, B_i \equiv B_{i(\text{FB})} = 6.311, 9.662, 10.726, 13.604, \text{ and } C_i \equiv C_{i(\text{FB})} = 10.357, 23.472, 29.36, 47.602.$$

The important numerical results of the above optical functions, at $T=0\text{K}$, $N = N_{\text{CDn(CDp)}}$, and for $E = E_{gni(gi)}$, are reported in following Tables 2a, 2b and 2c, and Tables 3a, 3b and 3c, in which they are also compared with the corresponding ones, calculated using from FB-PM [11], and also the relative deviations (RDs) of those numerical results, calculated using the corresponding data given by Aspnes and Studna [9], suggesting that our obtained numerical results of these optical coefficients are found to be more accurate than the corresponding ones, obtained from the FB-PM, as observed in Table 3c.

Table 2a. At the MIT, $T=0K$, $N=N_{CDn(p)}(r_{d(a)})$, and the critical photon energy $E_{CPE} = E = \mathbb{E}_{gni(gpi)}(r_{d(a)})$, $\kappa_{MIT}(\mathbb{E}_{gni(gpi)}, r_{d(a)}) = 0$, $\varepsilon_{2(MIT)}(\mathbb{E}_{gni(gpi)}, r_{d(a)}) = 0$, $\sigma_{O(MIT)}(\mathbb{E}_{gni(gpi)}, r_{d(a)}) = 0$ and $\alpha_{MIT}(\mathbb{E}_{gni(gpi)}, r_{d(a)}) = 0$, and the other functions such as : $n_{MIT}(\mathbb{E}_{gni(gpi)}, r_{d(a)})$, $\varepsilon_{1(MIT)}(\mathbb{E}_{gni(gpi)}, r_{d(a)})$, and $R_{MIT}(\mathbb{E}_{gni(gpi)}, r_{d(a)})$ decrease with increasing $r_{d(a)}$ and $\mathbb{E}_{gni}(r_{d(a)})$.

Donor		P	As	Te	Sb	Sn
At the MIT, $T=0K$, $N=N_{CDn}(r_d)$, and the critical photon energy $E_{CPE} = E = \mathbb{E}_{gni}(r_a)$, on has :						
$\mathbb{E}_{gni}(r_d)$ in meV	↗	1424	1424.3	1426	1428	1429
$n_{MIT}(\mathbb{E}_{gni}, r_d)$	↘	3.038	3.0173	2.9002	2.8553	2.8095
$\kappa_{MIT}(\mathbb{E}_{gni}, r_d)$		0	0	0	0	0
$\varepsilon_{1(MIT)}(\mathbb{E}_{gni}, r_d)$	↘	9.2294	9.1041	8.4109	8.1530	7.8931
$\varepsilon_{2(MIT)}(\mathbb{E}_{gni}, r_d)$		0	0	0	0	0
$\sigma_{O(MIT)}(\mathbb{E}_{gni}, r_d)$		0	0	0	0	0
$\alpha_{MIT}(\mathbb{E}_{gni}, r_d)$		0	0	0	0	0
$R_{MIT}(\mathbb{E}_{gni}, r_d)$	↘	0.2547	0.2522	0.2374	0.2316	0.2256

Acceptor		Ga(Al)	Mg	In
At the MIT, $T=0K$, $N=N_{CDp}(r_a)$, and the critical photon energy $E_{CPE} = E = \mathbb{E}_{gpi}(r_a)$, on has :				
$\mathbb{E}_{gpi}(r_a)$ in meV	↗	1420	1423.8	1424
$n_{MIT}(\mathbb{E}_{gpi}, r_a)$	↘	3.1015	3.0410	3.0380
$\kappa_{MIT}(\mathbb{E}_{gpi}, r_a)$		0	0	0
$\varepsilon_{1(MIT)}(\mathbb{E}_{gpi}, r_a)$	↘	9.6192	9.2478	9.2294
$\varepsilon_{2(MIT)}(\mathbb{E}_{gpi}, r_a)$		0	0	0
$\sigma_{O(MIT)}(\mathbb{E}_{gpi}, r_a)$		0	0	0
$\alpha_{MIT}(\mathbb{E}_{gpi}, r_a)$		0	0	0
$R_{MIT}(\mathbb{E}_{gpi}, r_a)$	↘	0.2625	0.551	0.2547

Table 2b. In d(a)-InP systems, the values of the following optical coefficients at $\mathbb{E} \leq 0$, expressed as functions of $r_{d(a)}$, and calculated using Equations (31-36, 24), for $E^* = \mathbb{E}_{gni(gpi)}(r_{d(a)})$, present the exponential tail-states for κ^{EEC-T} , ε_2^{ElmD-T} , σ_0^{EOC-T} , σ_0^{EOC-T} , α^{EOAC-T} and R^{NIR-T} , and their variations with increasing $r_{d(a)}$ are represented by the arrows: ↗ and ↘, suggesting that the obtained results of n^{ERI-T} , ε_1^{EReD-T} , and R^{NIR-T} are almost equal to the corresponding ones given in the above Table 2a.

d-GaAs systems		P	As	Te	Sb	Sn
$n^{ERI-T}(r_d)$	↘	3.0380	3.0173	2.9002	2.8553	2.8095
$\kappa^{EEC-T}(r_d)$	↗	0.1554	0.1555	0.1561	0.1568	0.1572
$\varepsilon_1^{EReD-T}(r_d)$	↘	9.2052	9.0799	8.3866	8.1284	7.8684
$\varepsilon_2^{ElmD-T}(r_d)$	↘	0.9439	0.9382	0.9054	0.8957	0.8834
$\sigma_0^{EOC-T}(r_d)$ in $\Omega^{-1}cm^{-1}$	↘	14.387	14.302	13.819	13.689	13.511
$\alpha^{EOAC-T}(r_d)$ in $10^3 cm^{-1}$	↗	22.418	22.439	22.557	22.696	22.766
$R^{NIR-T}(r_d)$	↘	0.2558	0.2533	0.2386	0.2329	0.2269

a-GaAs systems		Ga(Al)	Mg	In
$n^{ERI-T}(r_a)$	\searrow	3.1015	3.0410	3.0380
$\kappa^{EEC-T}(r_a)$	\nearrow	0.1539	0.1553	0.1554
$\varepsilon_1^{EReD-T}(r_a)$	\searrow	9.5955	9.2237	9.2052
$\varepsilon_2^{ElmD-T}(r_a)$	\searrow	0.9545	0.9444	0.9439
$\sigma_0^{EOC-T}(r_a)$	in $\Omega^{-1}cm^{-1}$	\searrow	14.507	14.392
$\alpha^{EOAC-T}(r_a)$	in $10^3 cm^{-1}$	\nearrow	22.144	22.405
$R^{NIR-T}(r_a)$	\searrow	0.264	0.256	0.2558

Table 2c. Here, the choice of the real refraction index: $n(E \rightarrow \infty, r_{d(a)}) = n_\infty(r_{d(a)}) = \sqrt{\varepsilon(r_{d(a)})} \times \frac{\omega_T}{\omega_L}$, $\omega_T = 5.3 \times 10^{13} s^{-1}$ [5] and $\omega_L = 1.1023 \times 10^{14} s^{-1}$, obtained from the Lyddane-Sachs-Teller relation [5], from which T(L) represents the transverse (longitudinal) optical phonon mode, giving rise to $n_\infty(r_p) = 1.6999$, and further, that of the asymptotic behavior, given for the extinction coefficient: $\kappa_\infty(E \rightarrow \infty, r_{d(a)}) \rightarrow 0$, as E^{-1} , so that $\sigma_0(E \rightarrow \infty, r_{d(a)})$ and $\alpha(E \rightarrow \infty, r_{d(a)})$ both go to their appropriate limiting constants, are found to be very important, affecting strongly the numerical results of the other optical coefficients.

Donor		P	As	Te	Sb	Sn
$\varepsilon(r_d)$	\searrow	12.5	12.20	10.57	9.987	9.40
$n_\infty(r_d)$	\searrow	1.6999	1.6794	1.5632	1.5195	1.4741
$\kappa_\infty(r_d)$		0	0	0	0	0
$\varepsilon_{1,\infty}(r_d)$	\searrow	2.8898	2.8204	2.4436	2.3088	2.1731
$\varepsilon_{2,\infty}(r_d)$		0	0	0	0	0
$\sigma_{0,\infty}(r_d)$	in $\frac{10^5}{\Omega \times cm}$	\searrow	7.7441	7.6506	7.1212	6.9220
$\alpha_\infty(r_d)$	in $(10^9 \times cm^{-1})$		2.1566	2.1566	2.1566	2.1566
$R_\infty(r_d)$	\searrow	0.0672	0.0643	0.0483	0.0425	0.0367

Acceptor		Ga(Al)	Mg	In
$\varepsilon(r_a)$	\searrow	13.418	12.543	12.5
$n_\infty(r_a)$	\searrow	1.7612	1.7029	1.6999
$\kappa_\infty(r_a)$		0	0	0
$\varepsilon_{1,\infty}(r_a)$	\searrow	3.1020	2.8997	2.8898
$\varepsilon_{2,\infty}(r_a)$		0	0	0
$\sigma_{0,\infty}(r_a)$	in $\frac{10^5}{\Omega \times cm}$	\searrow	8.0234	7.7574
$\alpha_\infty(r_a)$	in $(10^9 \times cm^{-1})$		2.1566	2.1566
$R_\infty(r_a)$	\searrow	0.076	0.068	0.067

Table 3a. In the P-InP system, at T=0K, our numerical results of the following optical coefficients, expressed as functions of E, and calculated using Equations (24, 25, 28, 29), for $E_{gn}(r_p) = E_{gni}(r_p) [= 1.4240 \text{ eV}]$, and the corresponding ones, obtained from the FB-model [11], are reported in the following Table 2a, in which the relative deviations (RDs) of those are also given and calculated, for $1.5 \leq E(\text{eV})$, using the Aspnes-and-Studna (AS)-data [9]. Here, as noted in above Table 2c, one obtains: $\kappa_{\infty}(E \rightarrow \infty, r_p) \rightarrow 0$ and $\varepsilon_{2,\infty}(E \rightarrow \infty, r_p) \rightarrow 0$, while, in the FB-model, $\kappa_{\infty(\text{FB})}(E \rightarrow \infty, r_p) = 0.3079$ and $\varepsilon_{2,\infty(\text{FB})}(E \rightarrow \infty, r_p) = 1.3275$.

E in eV	n (RD%)	κ (RD%)	ε_1 (RD%)	ε_2 (RD%)	n_{FB} (RD%)	κ_{FB} (RD%)	$\varepsilon_{1(FB)}$ (RD%)	$\varepsilon_{2(FB)}$ (RD%)
1.5	3.081 (10.9)	0.138 (32.1)	9.472 (20.4)	0.849 (39.4)	3.088 (10.6)	0.0037 (98.2)	9.537 (19.9)	0.023 (98.4)
1.6	3.142 (9.4)	0.162 (25.9)	9.844 (17.8)	1.015 (32.7)	3.147 (9.2)	0.008 (96.1)	9.902 (17.3)	0.053 (96.5)
1.7	3.208 (7.7)	0.186 (23.3)	10.260 (14.7)	1.191 (29.1)	3.211 (7.6)	0.016 (93.4)	10.310 (14.2)	0.103 (93.9)
1.8	3.282 (6.0)	0.212 (21.4)	10.725 (11.5)	1.393 (26.2)	3.281 (6.0)	0.027 (89.9)	10.766 (11.2)	0.179 (90.5)
1.9	3.362 (4.4)	0.243 (17.0)	11.247 (8.4)	1.635 (20.7)	3.359 (4.5)	0.043 (85.2)	11.279 (8.2)	0.291 (85.9)
2	3.451 (2.7)	0.279 (11.9)	11.834 (5.3)	1.927 (14.4)	3.444 (3.0)	0.066 (79.2)	11.855 (5.1)	0.455 (79.8)
2.1	3.549 (0.9)	0.322 (7.2)	12.495 (1.9)	2.285 (8.1)	3.537 (1.3)	0.097 (71.9)	12.504 (1.8)	0.689 (72.3)
2.2	3.657 (0.8)	0.373 (1.8)	13.237 (1.6)	2.729 (0.9)	3.640 (0.3)	0.140 (63.0)	13.229 (1.6)	1.022 (62.9)
2.3	3.775 (2.5)	0.434 (4.4)	14.063 (5.1)	3.280 (7.2)	3.751 (1.9)	0.199 (52.2)	14.033 (4.9)	1.493 (51.2)
2.4	3.902 (4.2)	0.508 (11.2)	14.967 (8.4)	3.965 (15.8)	3.871 (3.3)	0.278 (39.1)	14.904 (7.9)	2.153 (37.1)
2.5	4.035 (5.7)	0.596 (16.7)	15.928 (11.3)	4.812 (23.2)	3.995 (4.6)	0.384 (24.8)	15.810 (10.5)	3.069 (21.4)
2.6	4.169 (6.8)	0.483 (16.5)	17.149 (15.1)	4.031 (10.9)	4.118 (5.5)	0.524 (9.5)	16.679 (11.9)	4.317 (4.6)
2.7	4.293 (7.2)	0.662 (0.7)	17.992 (15.4)	5.684 (6.5)	4.228 (5.6)	0.705 (5.7)	17.381 (11.5)	5.961 (11.7)
2.8	4.390 (6.5)	0.886 (12.8)	18.484 (12.9)	7.782 (20.0)	4.310 (4.6)	0.929 (18.2)	17.709 (8.2)	8.010 (23.6)
2.9	4.436 (4.2)	1.152 (19.5)	18.354 (6.8)	10.222 (24.6)	4.339 (2.0)	1.192 (23.6)	17.410 (12.9)	10.343 (26.0)
3	4.409 (0.3)	1.440 (15.5)	17.369 (2.2)	12.700 (15.9)	4.295 (2.03)	1.472 (18.0)	16.283 (8.3)	12.647 (15.4)
3.1	4.297 (2.7)	1.715 (1.1)	15.518 (5.9)	14.742 (3.8)	4.167 (5.6)	1.735 (0.002)	14.352 (12.9)	14.462 (5.6)
3.2	4.108 (3.3)	1.937 (9.6)	13.124 (17.1)	15.912 (6.6)	3.966 (0.2)	1.941 (9.4)	11.965 (6.7)	15.396 (9.7)
3.3	3.878 (8.4)	2.074 (6.1)	10.735 (35.7)	16.087 (1.8)	3.729 (4.3)	2.061 (6.7)	9.657 (22.1)	15.372 (2.7)
3.4	3.650 (10.6)	2.123 (3.1)	8.814 (32.8)	15.500 (14.0)	3.498 (6.0)	2.094 (16.3)	7.854 (18.3)	14.648 (7.8)
3.5	3.460 (8.3)	2.102 (7.9)	7.551 (18.0)	14.542 (16.9)	3.308 (3.6)	2.058 (5.6)	6.706 (4.8)	13.614 (9.4)
3.6	3.324 (6.1)	2.037 (8.8)	6.900 (9.3)	13.547 (15.5)	3.174 (1.3)	1.982 (5.9)	6.144 (2.7)	12.582 (7.2)
3.7	3.247 (4.6)	1.956 (7.7)	6.718 (6.1)	12.706 (12.8)	3.098 (0.2)	1.892 (4.2)	6.018 (4.9)	11.723 (4.1)
3.8	3.224 (4.2)	1.878 (5.9)	6.867 (6.8)	12.109 (10.3)	3.075 (0.6)	1.806 (1.9)	6.190 (3.8)	11.108 (1.2)
3.9	3.247 (4.5)	1.816 (4.1)	7.243 (9.5)	11.792 (8.8)	3.096 (0.4)	1.738 (0.3)	6.563 (0.8)	10.761 (0.7)
4	3.308 (5.3)	1.780 (2.9)	7.777 (13.1)	11.779 (8.3)	3.154 (0.4)	1.696 (2.0)	7.073 (2.9)	10.699 (1.6)
4.1	3.404 (6.5)	1.780 (2.6)	8.418 (16.8)	12.115 (9.3)	3.244 (1.5)	1.688 (2.7)	7.674 (6.5)	10.955 (1.2)
4.2	3.527 (7.7)	1.825 (3.6)	9.106 (19.5)	12.875 (11.6)	3.360 (2.6)	1.725 (2.1)	8.314 (9.1)	11.594 (0.5)
4.3	3.670 (8.4)	1.932 (5.8)	9.734 (19.9)	14.184 (14.8)	3.495 (3.3)	1.820 (0.3)	8.899 (9.6)	12.723 (3.0)
4.4	3.817 (8.2)	2.122 (8.9)	10.069 (16.5)	16.204 (17.9)	3.633 (3.0)	1.994 (2.3)	9.225 (6.7)	14.486 (5.4)
4.5	3.935 (6.4)	2.420 (10.7)	9.625 (8.3)	19.048 (17.9)	3.743 (1.3)	2.269 (3.8)	8.866 (0.3)	16.987 (5.1)
4.6	3.952 (4.0)	2.840 (7.7)	7.555 (0.9)	22.450 (12.0)	3.761 (1.0)	2.659 (0.8)	7.072 (5.5)	19.998 (0.2)
4.7	3.764 (5.7)	3.336 (3.5)	3.044 (32.8)	25.112 (9.4)	3.585 (0.7)	3.121 (3.2)	3.114 (35.9)	22.376 (2.5)
4.8	3.306 (10.8)	3.747 (6.5)	-3.108 (10.4)	24.775 (18.0)	3.155 (5.7)	3.502 (0.4)	-2.310 (33.4)	22.101 (5.3)
4.9	2.694 (5.8)	3.882 (10.5)	-7.811 (33.1)	20.911 (16.9)	2.581 (1.4)	3.620 (3.0)	-6.446 (9.8)	18.687 (4.4)
5	2.164 (1.6)	3.732 (6.8)	-9.245 (20.4)	16.158 (8.5)	2.088 (2.0)	3.469 (0.7)	-7.675 (0.4)	14.484 (2.8)
5.1	1.834 (4.5)	3.462 (5.2)	-8.624 (10.7)	12.699 (10.6)	1.783 (2.2)	3.205 (2.6)	-7.094 (0.4)	11.433 (0.4)
5.2	1.661 (6.6)	3.205 (6.2)	-7.510 (12.6)	10.647 (13.3)	1.628 (4.5)	2.957 (2.0)	-6.092 (8.6)	10.944 (16)
5.3	1.571 (6.0)	3.001 (7.1)	-6.537 (15.6)	9.428 (13.5)	1.549 (4.5)	2.760 (1.5)	-5.221 (7.6)	8.551 (2.9)
5.4	1.514 (4.0)	2.844 (7.2)	-5.794 (17.9)	8.610 (11.6)	1.500 (3.1)	2.609 (1.6)	-4.557 (7.3)	7.830 (1.5)
5.5	1.470 (3.1)	2.715 (6.0)	-5.209 (15.0)	7.983 (9.2)	1.464 (2.7)	2.486 (3.0)	-4.036 (11)	7.278 (0.4)
5.6	1.436 (4.4)	2.602 (4.8)	-4.709 (10)	7.474 (9.4)	1.436 (4.4)	2.378 (4.3)	-3.592 (16.1)	6.828 (0.5)
5.7	1.413 (6.7)	2.501 (4.9)	-4.256 (8.5)	7.068 (11.9)	1.418 (7.0)	2.281 (4.3)	-3.192 (18.7)	6.467 (2.4)
5.8	1.402 (8.0)	2.411 (5.7)	-3.846 (9.6)	6.762 (14.1)	1.411 (8.6)	2.195 (3.7)	-2.828 (19.4)	6.192 (4.5)
5.9	1.402 (7.8)	2.335 (7.0)	-3.487 (13.5)	6.550 (15.3)	1.413 (8.6)	2.122 (2.8)	-2.507 (18.4)	5.999 (5.6)

6	1.410 (5.5)	2.276 (7.7)	-3.192 (19.1)	6.417 (13.7)	1.422 (6.5)	2.065 (2.3)	-2.241 (17.8)	5.875 (4.1)
...								
10²¹	1.6999	0	2.8898	0	1.766	0.3006	3.0284	1.0616
...								
10²²	1.6999	0	2.8898	0	1.766	0.3006	3.0284	1.0616

E in eV	n (RD%)	κ (RD%)	ε_1 (RD%)	ε_2 (RD%)	n_{FB} (RD%)	κ_{FB} (RD%)	$\varepsilon_{1(FB)}$ (RD%)	$\varepsilon_{2(FB)}$ (RD%)
---------	-----------	----------------	-----------------------	-----------------------	----------------	---------------------	-----------------------------	-----------------------------

Table 3b. In the P-InP system, at T=0K, our numerical results of the following optical coefficients, expressed as functions of E, and calculated using Equations (24, 25, 28, 29), for $\mathbb{E}_{gn}(r_p) = \mathbb{E}_{gni}(r_p)[= 1.5198 \text{ eV}]$, and the corresponding ones, obtained from the FB-model [11], are reported in the following Table 2a, in which the relative deviations (RDs) of those are also given and calculated, for $1.6 \leq E(\text{eV})$, using the Aspnes-and-Studna (AS)-data [9]. Here, as noted in above Table 2c, one obtains: $\alpha_\infty(E \rightarrow \infty, r_p) = 2.1602 \times 10^9 \text{ cm}^{-1}$ and $\sigma_{0,\infty}(E \rightarrow \infty, r_p) = 9.4912 \times 10^5 \left(\frac{1}{\Omega \times \text{cm}}\right)$, while, in the FB-model, $\alpha_{FB} \rightarrow \infty$, and $\sigma_{0(FB)} \rightarrow \infty$, which should be not correct.

E in eV	$\alpha (10^3 \times \text{cm}^{-1}); \text{RD}\%$	R; RD%	$\sigma_o \left(\frac{1}{\Omega \times \text{cm}}\right)$	$\sigma_{o(FB)} \left(\frac{1}{\Omega \times \text{cm}}\right)$	$\alpha_{FB} (10^3 \times \text{cm}^{-1}); \text{RD}\%$	$R_{FB}; \text{RD}\%$
1.5	20.946; 32.0	0.261; 15.5	13.631	0.367	0.563; 98.2	0.261; 14.5
1.6	26.203; 25.8	0.268; 12.5	17.389	0.911	1.371; 96.1	0.2680; 12.7
1.7	31.97; 23.2	0.277; 10.1	21.670	1.870	2.756; 93.4	0.2757; 10.5
1.8	38.73; 21.5	0.2857; 7.8	26.847	3.444	4.969; 89.9	0.2840; 8.4
1.9	46.80; 17.1	0.2955; 5.6	33.243	5.926	8.352; 85.2	0.2929; 6.4
2	56.57; 12.0	0.3060; 3.5	41.248	9.737	13.38; 79.2	0.3026; 4.5
2.1	68.51; 7.3	0.3175; 1.4	51.366	15.490	20.73; 71.9	0.3130; 2.8
2.2	83.16; 1.7	0.3299; 0.9	64.252	24.072	31.31; 63.0	0.3243; 0.8
2.3	101.25; 4.5	0.3432; 3.1	80.743	36.751	46.398; 52.1	0.3365; 1.0
2.4	123.58; 11.1	0.3574; 4.8	101.86	55.310	67.65; 39.2	0.3495; 2.5
2.5	151.04; 16.6	0.3722; 6.6	128.75	82.133	97.33; 24.9	0.3633; 4.1
2.6	127.38; 16.6	0.3813; 5.9	112.18	120.14	138.13; 9.5	0.3776; 4.9
2.7	181.13; 0.7	0.3965; 6.6	164.26	172.28	192.88; 5.7	0.3923; 5.5
2.8	251.51; 12.7	0.4115; 6.6	233.22	240.06	263.70; 18.1	0.4067; 5.4
2.9	338.58; 19.5	0.4254; 5.3	317.29	321.03	350.23; 23.6	0.4200; 4.0
3	437.82; 15.4	0.4371; 2.4	407.81	406.08	447.55; 18.0	0.4312; 1.0
3.1	538.93; 1.2	0.4455; 1.9	489.13	479.85	545.16; 0.02	0.4390; 3.3
3.2	628.07; 9.7	0.4494; 1.9	545.01	527.34	629.40; 9.5	0.4420; 3.5
3.3	693.67; 6.1	0.4479; 0.4	568.21	542.94	689.27; 6.7	0.4395; 14.6
3.4	731.57; 3.0	0.4413; 5.3	564.05	533.05	721.36; 1.6	0.4316; 3.0
3.5	745.46; 7.8	0.4306; 6.9	544.78	510.00	729.91; 5.6	0.4195; 4.1
3.6	743.31; 8.8	0.4181; 6.9	521.97	484.80	723.13; 5.9	0.4054; 3.7
3.7	733.55; 7.7	0.4060; 6.0	503.20	464.26	709.43; 4.2	0.3918; 2.3
3.8	723.21; 5.9	0.3965; 4.9	492.52	451.81	695.64; 1.9	0.3809; 0.8
3.9	717.71; 4.1	0.3912; 4.0	492.22	449.22	686.92; 0.4	0.3745; 0.4
4	721.60; 2.9	0.3910; 4.0	504.31	458.08	687.48; 2.0	0.3734; 0.7
4.1	739.43; 2.6	0.3965; 4.3	531.65	480.76	701.53; 2.7	0.3780; 0.5
4.2	776.93; 3.6	0.4079; 5.4	578.81	521.21	734.31; 2.1	0.3887; 0.4
4.3	842.10; 5.8	0.4253; 6.3	652.82	585.58	793.26; 0.3	0.4056; 1.4
4.4	946.33; 8.9	0.4490; 7.2	763.12	682.23	888.95; 2.3	0.4288; 2.3
4.5	1103.7; 10.7	0.4790; 6.7	917.43	818.18	1034.7; 3.8	0.4584; 2.1
4.6	1323.9; 7.7	0.5149; 4.4	1105.3	984.61	1239.5; 0.8	0.4941; 0.2
4.7	1588.7; 3.5	0.5548; 2.2	1263.3	1125.6	1486.4; 3.2	0.5338; 1.7
4.8	1822.6; 6.5	0.5941; 2.9	1272.8	1135.5	1703.6; 0.4	0.5726; 0.7
4.9	1927.5; 10.4	0.6247; 5.7	1096.7	980.07	1797.7; 3.0	0.6019; 1.8

5	1891.1; 6.7	0.6384; 4.1	864.69	775.15	1757.7; 0.8	0.6128; 0.03
5.1	1789.4; 5.2	0.6335; 2.2	693.17	624.11	1656.7; 2.6	0.6042; 2.5
5.2	1688.7; 6.2	0.6170; 2.7	592.57	535.74	1558.0; 2.0	0.5839; 2.8
5.3	1611.7; 7.1	0.5976; 3.6	534.81	485.10	1482.7; 1.5	0.5611; 2.7
5.4	1556.1; 7.2	0.5796; 4.6	497.62	452.58	1427.9; 1.6	0.5405; 2.4
5.5	1513.2; 5.9	0.5635; 4.0	469.95	428.44	1385.5; 3.0	0.5220; 3.7
5.6	1476.7; 4.7	0.5479; 2.6	448.00	409.27	1349.4; 4.3	0.5043; 5.5
5.7	1444.5; 4.9	0.5319; 1.9	431.20	394.54	1317.4; 4.3	0.4867; 6.8
5.8	1417.0; 5.7	0.5157; 2.3	419.78	384.40	1290.1; 3.7	0.4691; 6.9
5.9	1396.2; 6.9	0.5003; 3.6	413.62	378.82	1269.0; 2.8	0.4527; 6.3
6	1383.8; 7.7	0.4867; 5.6	412.09	377.29	1255.7; 2.3	0.4385; 4.9
...						
10^{21}	2.1566×10^6	0.0672	7.7441×10^5	1.1363×10^{22}	3.046×10^{22}	0.0875
...						
10^{22}	2.1566×10^6	0.0672	7.7441×10^5	1.1363×10^{23}	3.046×10^{23}	0.0875
<hr/>						
E in eV	$\alpha (10^3 \times cm^{-1}); RD\%$	R; RD%	$\sigma_o \left(\frac{1}{\Omega \times cm} \right)$	$\sigma_{O(FB)} \left(\frac{1}{\Omega \times cm} \right)$	$\alpha_{FB} (10^3 \times cm^{-1}); RD\%$	$R_{FB}; RD\%$
<hr/>						

Table 3c. Here, our maximal relative deviation (MRD)-values and those of $(MRD)_{FB}$, calculated using the (AS)-data [9], are reported, suggesting that our obtained numerical results of these optical coefficients are found be more accurate than the corresponding ones, obtained from the FB-model.

MRD	n	κ	ϵ_1	ϵ_2	α	R
E (eV)						
1.5	10.9%	32.1%		39.4%	32%	15.5%
3.3			35.7%			
$(MRD)_{FB}$	n_{FB}	κ_{FB}	$\epsilon_{1(FB)}$	$\epsilon_{2(FB)}$	α_{FB}	R_{FB}
E (eV)						
1.5	10.6%	98.2%		98.4%	98.2%	14.5%
4.7			35.9%			

Some important cases, given in various physical conditions, are considered as follows.

5.1. Metal-insulator transition (MIT)-case

As discussed in Equations (21-23) and Eq. (A4) of the Appendix A, the physical conditions used for the MIT are: $T=0K$, $N^* = 0$ or $N = N_{CDn(CDp)} \cong N_{CDn(CDp)}^{EBT}$, vanishing the Fermi energy:

$$\mathbb{E}_{Fno(Fpo)}(N^*) \equiv \frac{\hbar^2 \times k_{Fn(Fp)}^2(N^*)}{2 \times m_{n(p)}^*} = 0. \text{ Further, from the discussions given Eq. (5) for the optical band gap:}$$

$$\mathbb{E}_{gn1(gp1)}(N^* = 0, r_{d(a)}, T = 0) = \mathbb{E}_{gnei(gpei)}(r_{d(a)}) = \mathbb{E}_{gni(gpi)}(r_{d(a)}), \text{ according also to the MIT.}$$

Then, in this MIT-case, replacing both $\mathbb{E}_{\text{gnei}(\text{gpei})}$ and $\mathbb{E}_{\text{gn1}(\text{gp1})}$, by $\mathbb{E}_{\text{gni}(\text{gpi})}$, given in Equations (28, 29), and consequently from Eq. (24), one gets, for the effective photon energy $E^* \equiv E - \mathbb{E}_{\text{gni}(\text{gpi})} = 0$:

$$\kappa(E^*, r_{d(a)}) = 0, \quad \varepsilon_2(E^*, r_{d(a)}) = 0, \quad \sigma_0(E^*, r_{d(a)}) = 0 \quad \text{and} \quad \alpha(E^*, r_{d(a)}) = 0, \quad \text{corresponding also to the MIT.}$$

Thus, in this case, the photon energy E becomes the critical photon energy, defined by:

$$E_{\text{CPE}}(r_{d(a)}) \equiv \mathbb{E}_{\text{gni}(\text{gpi})}(r_{d(a)}). \quad \text{Therefore, Equations (28, 29), obtained in the MIT-case, become:}$$

$$\kappa(E^* = 0) = f(E) \times \mathbb{E}_{\text{gni}(\text{gpi})}^{29/15} \times (E^* \equiv E - \mathbb{E}_{\text{gni}(\text{gpi})} = 0)^{1/15} = 0, \quad \text{and} \quad (30)$$

$$n(E = \mathbb{E}_{\text{gni}(\text{gpi})}) = n_{\infty}(r_{d(a)}) + \sum_{i=1}^4 \frac{B_{oi}E + C_{oi}}{E^2 - B_iE + C_i}, \quad \text{in which } \mathbb{E}_{\text{gnei}(\text{gpei})} = \mathbb{E}_{\text{gni}(\text{gpi})}. \quad (31)$$

Then, going back to the remark given in Eq. (23), we can determine the values of some optical coefficients for $\mathbb{E} \leq 0$, representing the exponential tail-states, which can be deduced from Eq. (30), by putting: $E^* =$

$$\kappa^{\text{EEC-T}}(\mathbb{E}_{\text{gni}(\text{gpi})}) = f(\mathbb{E}_{\text{gni}(\text{gpi})}) \times \mathbb{E}_{\text{gni}(\text{gpi})}^2. \quad (32)$$

Now, replacing Equations (31, 32) into Equations (24, 25), one obtains for $\mathbb{E} \leq 0$ the expressions, given for the following exponential tail-states of ε_2 , $\sigma_0(E)$, α , and R as:

$$\varepsilon_2^{\text{ElmDC-T}}(\mathbb{E}_{\text{gni}(\text{gpi})}) = 2 \times \kappa^{\text{EEC-T}}(\mathbb{E}_{\text{gni}(\text{gpi})}) \times n(E = \mathbb{E}_{\text{gni}(\text{gpi})}), \quad (33)$$

$$\sigma_0^{\text{EOC-T}}(\mathbb{E}_{\text{gni}(\text{gpi})}) = \frac{\varepsilon_{\text{free space}} \times \mathbb{E}_{\text{gni}(\text{gpi})} \times \varepsilon_2^{\text{ElmDC-T}}(\mathbb{E}_{\text{gni}(\text{gpi})})}{4\pi\hbar}, \quad (34)$$

$$\alpha^{\text{EOAC-T}}(\mathbb{E}_{\text{gni}(\text{gpi})}) = \frac{2 \times \mathbb{E}_{\text{gni}(\text{gpi})} \times \kappa^{\text{EEC-T}}(\mathbb{E}_{\text{gni}(\text{gpi})})}{\hbar \times c}, \quad \text{and} \quad (35)$$

$$R^{\text{NIR-T}}(\mathbb{E}_{\text{gni}(\text{gpi})}) = \frac{[n(\mathbb{E}_{\text{gni}(\text{gpi})}) - 1]^2 + \kappa^{\text{EEC-T}}(\mathbb{E}_{\text{gni}(\text{gpi})})^2}{[n(\mathbb{E}_{\text{gni}(\text{gpi})}) + 1]^2 + \kappa^{\text{EEC-T}}(\mathbb{E}_{\text{gni}(\text{gpi})})^2}. \quad (36)$$

The numerical results of those optical functions, determined by Equations (31-36, 24), were discussed and reported in the above Table 2b.

5.2. Extrema values of $\varepsilon_{1(2)}$ as functions of photon energy E

From Equations (24, 28, 29), we can determine the extrema values of typical optical functions $\varepsilon_{1(2)}(E, r_{d(a)})$ in following physical conditions by: $T=0\text{K}$ and $N = N_{\text{CDn}}(N_{\text{Dp}})$, and by: $T=20\text{K}$ and $N = 10^{20}\text{cm}^{-3}$, respectively, as given in following Tables 4n and 4p, in which the arrows ($\uparrow \downarrow$) indicates the maximum, and ($\downarrow \uparrow$) the minimum and the extrema-values of those occur at the same corresponding photon energy E .

Table 4n. In d-InP systems, and for two types of physical conditions such as: ($T=0\text{K}$ and $N = N_{\text{CDn}}(r_d)$) and ($T=20\text{K}$, $N = 10^{20}\text{cm}^{-3}$), the extrema values of $\varepsilon_1(E)$ and $\varepsilon_2(E)$, calculated using Equations (24, 28, 29), vary with increasing E , represented by the arrows: \uparrow or \downarrow , suggesting that those extrema occur at the same E .

E in eV	2.5	2.8	3	3.2	3.7	4.4	4.7	5	10	100	10 ²¹
In the P- GaAs system, at $T=0\text{K}$ and $N = N_{\text{CDn}}(r_p) = 2.09 \times 10^{16}\text{cm}^{-3}$, $\mathbb{E}_{\text{gn}}(r_p) \equiv \mathbb{E}_{\text{gni}}(r_p)[= 1.424\text{ eV}]$											
$\varepsilon_1(E)$	15.93	\uparrow 18.48	\downarrow 17.37	13.12	\downarrow 6.72	\uparrow 10.07	\downarrow 3.04	\downarrow -9.24	\uparrow 0.15	2.62	2.8898
$\varepsilon_2(E)$	4.81	7.78	12.70	\uparrow 15.91	\downarrow 12.71	\uparrow 16.20	\uparrow 25.11	\downarrow 16.16	\downarrow 1.76	1.24	0
In the As-GaAs system, at $T=0\text{K}$ and $N = N_{\text{CDn}}(r_{As}) = 2.25 \times 10^{16}\text{cm}^{-3}$, $\mathbb{E}_{\text{gn}}(r_{As}) \equiv \mathbb{E}_{\text{gni}}(r_{As})[= 1.4243\text{ eV}]$											
$\varepsilon_1(E)$	15.76	\uparrow 18.30	\downarrow 17.18	12.95	\downarrow 6.59	\uparrow 9.91	\downarrow 2.89	\downarrow -9.33	\uparrow 0.12	2.55	2.8204
$\varepsilon_2(E)$	4.79	7.74	12.63	\uparrow 15.83	\downarrow 12.62	\uparrow 16.11	\uparrow 24.97	\downarrow 16.00	\downarrow 1.72	1.23	0

In the Te- GaAs system, at $T=0\text{K}$ and $N = N_{\text{CDn}}(r_{Te}) = 3.456 \times 10^{16}\text{cm}^{-3}$, $\mathbb{E}_{\text{gn}}(r_{Te}) \equiv \mathbb{E}_{\text{gni}}(r_{Te})[= 1.426\text{ eV}]$

$\varepsilon_1(E)$	14.81	↑	17.27	↓	16.16	12.02	↓	5.86	↑	9.05	↓	2.05	↓	-9.78	↑	-0.09	2.18	2.4436		
$\varepsilon_2(E)$	4.66		7.51		12.26	↑	15.34	↓	12.15	↑	15.60	↑	24.16	↓	15.13	↓	1.52	1.14	0	
In the Sb- GaAs system, at T=0K and $N = N_{CDn}(r_{Sb}) = 4.1 \times 10^{16} \text{ cm}^{-3}$, $\mathbb{E}_{gn}(r_{Sb}) \equiv \mathbb{E}_{gni}(r_{Sb})[= 1.428 \text{ eV}]$																				
$\varepsilon_1(E)$	14.44	↑	16.87	↓	15.77		11.70	↓	5.60	↑	8.73	↓	1.76	↓	-9.92	↑	-0.16	2.05	2.3088	
$\varepsilon_2(E)$	4.61		7.40		12.10	↑	15.13	↓	11.95	↑	15.39	↑	23.84	↓	14.79	↓	1.44	1.11	0	
In the Sn- GaAs system, at T=0K and $N = N_{CDn}(r_{Sn}) = 4.91 \times 10^{16} \text{ cm}^{-3}$, $\mathbb{E}_{gn}(r_{Sn}) \equiv \mathbb{E}_{gni}(r_{Sn})[= 1.429 \text{ eV}]$																				
$\varepsilon_1(E)$	14.08	↑	16.48	↓	15.38		11.31	↓	5.33	↑	8.41	↓	1.45	↓	-10.08	↑	-0.23	1.92	2.1731	
$\varepsilon_2(E)$	4.56		7.31		11.95	↑	14.93	↓	11.77	↑	15.18	↑	23.52	↓	14.45	↓	1.36	1.07	0	
E in eV	2.5		2.8		3		3.2		3.7		4.4		4.7		5		10	100	10^{21}	
In the P- GaAs system, at T=20K and $N = 10^{20} \text{ cm}^{-3}$, $\mathbb{E}_{gn}(r_P) \equiv \mathbb{E}_{gn1}(r_P)[= 2.4567 \text{ eV}]$																				
$\varepsilon_1(E)$	16.05		19.28	↑	19.42	↓	16.76	↓	10.20	↑	13.76	↓	11.72		1.12	↓	0.48	↑	2.62	2.8898
$\varepsilon_2(E)$	3.88	↓	0.48	↑	1.51		2.79		3.79		6.91	↑	11.77	↓	8.17		1.36	1.21	0	

In the As- GaAs system, at T=20K and $N = 10^{20} \text{ cm}^{-3}$, $\mathbb{E}_{gn}(r_{As}) \equiv \mathbb{E}_{gn1}(r_{As})[= 2.4525 \text{ eV}]$																				
$\varepsilon_1(E)$	15.89		19.09	↑	19.24	↓	16.59	↓	10.07	↑	13.59	↓	11.55		1.01	↓	0.44	↑	2.55	2.8204
$\varepsilon_2(E)$	3.89	↓	0.49	↑	1.52		2.80		3.79		6.90	↑	11.75	↓	8.12		1.33	1.20	0	

In the Te- GaAs system, at T=20K and $N = 10^{20} \text{ cm}^{-3}$, $\mathbb{E}_{gn}(r_{Te}) \equiv \mathbb{E}_{gn1}(r_{Te})[= 2.4254 \text{ eV}]$																				
$\varepsilon_1(E)$	14.93		18.06	↑	18.20	↓	15.62	↓	9.30	↑	12.67	↓	10.57		0.37	↓	0.22	↑	2.19	2.4436
$\varepsilon_2(E)$	3.89	↓	0.56	↑	1.63		2.92		3.82		6.88	↑	11.66	↓	7.85		1.18	1.12	0	

In the Sb- GaAs system, at T=20K and $N = 10^{20} \text{ cm}^{-3}$, $\mathbb{E}_{gn}(r_{Sb}) \equiv \mathbb{E}_{gn1}(r_{Sb})[= 2.415 \text{ eV}]$																				
$\varepsilon_1(E)$	14.55		17.66	↑	17.79	↓	15.25	↓	9.01	↑	12.32	↓	10.20		0.14	↓	0.15	↑	2.05	2.3088
$\varepsilon_2(E)$	3.89	↓	0.58	↑	1.67		2.97		3.82		6.86	↑	11.63	↓	7.74		1.13	1.08	0	

In the Sn- GaAs system, at T=20K and $N = 10^{20} \text{ cm}^{-3}$, $\mathbb{E}_{gn}(r_{Sn}) \equiv \mathbb{E}_{gn1}(r_{Sn})[= 2.4022 \text{ eV}]$																				
$\varepsilon_1(E)$	14.19		17.26	↑	17.39	↓	14.88	↓	8.72	↑	11.97	↓	9.81		-0.11	↓	0.08	↑	1.92	2.1731
$\varepsilon_2(E)$	3.88	↓	0.61	↑	1.73		3.03		3.84		6.87	↑	11.61	↓	7.65		1.07	1.05	0	
E in eV	2.5		2.8		3		3.2		3.7		4.4		4.7		5		10	100	10^{21}	

Table 4p. In a-InP systems, and for two types of physical conditions such as: (T=0K and $N = N_{CDp}(r_a)$) and (T=20K, $N = 10^{20} \text{ cm}^{-3}$), the extrema values of $\varepsilon_1(E)$ and $\varepsilon_2(E)$, calculated using Equations (24, 28, 29), vary with increasing E, represented by the arrows: ↑ or ↓, suggesting that their extrema occur at the same E.

E in eV	2.5		2.8		3		3.2		3.7		4.4		4.7		5		10	100	10 ²¹
In the Ga- InP system, at T=0K and N = N _{CDp} (r _{Ga}) = 1.692 x10 ¹⁸ cm ⁻³ , E _{gp} (r _{Ga}) ≡ E _{gpi} (r _{Ga})[= 1.42 eV]																			
ε ₁ (E)	16.49	↑	19.09	↓	17.95		13.64		7.10	↑	10.53	↓	3.47	↓	-9.05	↑	0.27	2.82	3.1020
ε ₂ (E)	4.87		7.95		12.96	↑	16.24	↓	12.99	↑	16.52	↑	25.59	↓	16.64		1.87	1.29	0
In the Mg- InP system, at T=0K and N = N _{CDp} (r _{Mg}) = 2.072 x10 ¹⁸ cm ⁻³ , E _{gp} (r _{Mg}) ≡ E _{gpi} (r _{Mg})[= 1.4238 eV]																			
ε ₁ (E)	15.95	↑	18.51	↓	17.40		13.15		6.74	↑	10.09	↓	3.06	↓	-9.23	↑	0.16	2.62	2.8997
ε ₂ (E)	4.81		7.79		12.71	↑	15.93	↓	12.72	↑	16.22	↑	25.13	↓	16.18		1.77	1.24	0
In- InP system, at T=0K and N = N _{CDp} (r _{In}) = 2.09 x10 ¹⁸ cm ⁻³ , E _{gp} (r _{In}) ≡ E _{gpi} (r _{In})[= 1.424 eV]																			
ε ₁ (E)	15.93	↑	18.48	↓	17.37		13.12		6.72	↑	10.07	↓	3.04	↓	-9.24	↑	0.156	2.617	2.8898
ε ₂ (E)	4.81		7.79		12.71	↑	15.93	↓	12.72	↑	16.22	↑	25.13	↓	16.18		1.77	1.24	0

E in eV	2.5	2.8	3	3.2	3.7	4.4	4.7	5	10	100	10 ²¹
In the Ga- InP system, at T=20K and N = 10 ²⁰ cm ⁻³ , $\mathbb{E}_{gp}(r_{Ga}) \equiv \mathbb{E}_{gp1}(r_{Ga}) [= 2.3822 \text{ eV}]$											
$\varepsilon_1(E)$	16.59	19.88	↑ 20.01	↓ 17.26	10.52	↑ 14.11	↓ 11.86	0.94	↓ 0.58	↑ 2.83	3.1020
$\varepsilon_2(E)$	4.20	↓ 0.73	↑ 1.98	3.43	4.34	7.57	↑ 12.78	↓ 8.89	1.47	1.26	0
In the Mg-InP system, at T=20K and N = 10 ²⁰ cm ⁻³ , $\mathbb{E}_{gp}(r_{Mg}) \equiv \mathbb{E}_{gp1}(r_{Mg}) [= 2.3690 \text{ eV}]$											
$\varepsilon_1(E)$	16.01	19.30	↑ 19.43	↓ 16.73	10.12	↑ 13.62	↓ 11.34	0.61	↓ 0.46	↑ 2.63	2.8998
$\varepsilon_2(E)$	4.18	↓ 0.76	↑ 2.04	3.49	4.35	7.55	↑ 12.72	↓ 8.76	1.40	1.22	0
In the In-InP system, at T=20K and N = 10 ²⁰ cm ⁻³ , $\mathbb{E}_{gp}(r_{In}) \equiv \mathbb{E}_{gp1}(r_{In}) [= 2.3683 \text{ eV}]$											
$\varepsilon_1(E)$	16.02	19.27	↑ 19.40	↓ 16.70	10.10	↑ 13.60	↓ 11.32	0.60	↓ 0.456	↑ 2.62	2.8898
$\varepsilon_2(E)$	4.181	↓ 0.77	↑ 2.041	3.49	4.35	7.55	↑ 12.72	↓ 8.75	1.39	1.22	0
E in eV	2.5	2.8	3	3.2	3.7	4.4	4.7	5	10	100	10 ²¹

5.3. Variations of various optical coefficients as functions of N, typically for some d(a)-InP systems

Also, from Equations (24, 28, 29), we can determine the variations of various optical coefficients at 20K, as functions of N, typically for E=3.2 eV and for some (P, Te, Sn)-InP systems and (Ga, In)- InP ones, being indicated by the arrows: ↗ and ↘, as tabulated in following Tables 5n and 5p, in which the physical condition $N > N_{CDn(NDp)}$ (or $N^* > 0$) must be respected, and their variations thus depend on the ones of the optical band gap, $\mathbb{E}_{gn1(gp1)}(N^*, r_{d(a)})$.

Table 5n. In (P, Te, Sn)- InP systems, our numerical results of the following optical coefficients, expressed as functions of N, and calculated using Equations (31-36, 24), for E=3.2 eV and T=20K, present the variations by arrows, (↘ and ↗), since those of the optical gap $\mathbb{E}_{gn1}(N^*, r_d)$ increase with increasing N, at T=20 K.

N (10 ¹⁸ cm ⁻³)	↗	4	8.5	15	50	80	100
$\mathbb{E}_{gn1}(N^*, r_P, 20K)$ in eV	↗	1.5059	1.5805	1.6714	2.0447	2.3016	2.4567
$n(r_P)=4.1086$							
$\kappa(N, r_P)$	↘	1.762	1.610	1.435	0.820	0.495	0.339
$\varepsilon_1(N, r_P)$	↗	13.775	14.287	14.823	16.209	16.635	16.766
$\varepsilon_2(N, r_P)$	↘	14.481	13.233	11.789	6.735	4.072	2.787
$\sigma_O(N, r_P)$ in 10 ² Ω ⁻¹ cm ⁻¹	↘	4.960	4.532	4.038	2.307	1.395	0.955
$\alpha(N, r_P)$ in 10 ⁵ cm ⁻¹	↘	5.715	5.222	4.652	2.658	1.607	1.100
$R(N, r_P)$	↘	0.437	0.427	0.416	0.386	0.376	0.373
$\mathbb{E}_{gn1}(N^*, r_{Te}, 20K)$ in eV	↗	1.4976	1.5692	1.6571	2.2012	2.2731	2.4254
$n(r_{Te})=3.9695$							
$\kappa(N, r_{Te})$	↘	1.779	1.633	1.462	0.853	0.527	0.368
$\varepsilon_1(N, r_{Te})$	↗	12.590	13.090	13.620	15.029	15.478	15.621
$\varepsilon_2(N, r_{Te})$	↘	14.127	12.964	11.604	6.774	4.188	2.925
$\sigma_O(N, r_{Te})$ in 10 ² Ω ⁻¹ cm ⁻¹	↘	4.839	4.440	3.974	2.320	1.434	1.002

$\propto (N, r_{Te})$ in $10^5 cm^{-1}$	\searrow	5.771	5.295	4.740	2.767	1.711	1.195
$R(N, r_{Te})$	\searrow	0.430	0.420	0.408	0.375	0.364	0.361
<hr/>							
$\mathbb{E}_{gn1}(N^*, r_{Sn}, 20K)$ in eV	\nearrow	1.4924	1.5616	1.6471	2.0040	2.2520	2.4022
$n(r_{Sn})=3.8768$							
$\kappa(N, r_{Sn})$	\searrow	1.791	1.648	1.481	0.878	0.552	0.391
$\varepsilon_1(N, r_{Sn})$	\nearrow	11.824	12.312	12.837	14.258	14.725	14.877
$\varepsilon_2(N, r_{Sn})$	\searrow	13.883	12.781	11.481	6.810	4.278	3.031
$\sigma_0(N, r_{Sn})$ in $10^2 \Omega^{-1}cm^{-1}$	\searrow	4.755	4.378	3.932	2.332	1.465	1.038
$\propto (N, r_{Sn})$ in $10^5 cm^{-1}$	\searrow	5.806	5.345	4.802	2.848	1.789	1.267
$R(N, r_{Sn})$	\searrow	0.425	0.415	0.403	0.368	0.356	0.352
<hr/>							
$N (10^{18} cm^{-3})$		4	8.5	15	50	80	100
<hr/>							

Table 5p. In (Ga, In)- InP systems, the numerical results of the following optical coefficients, expressed as functions of N, and calculated using Equations (31-36, 24), for E=3.2eV and T=20K, present the variations by arrows, (\searrow or \nearrow), since those of the optical gap $\mathbb{E}_{gp1}(N^*, r_a)$ increase with increasing N, at T=20 K.

$N (10^{18} cm^{-3})$	15		26		60		100
<hr/>							
$\mathbb{E}_{gp1}(N^*, r_{Ga}, 20K)$ in eV	1.6260	\nearrow	1.7533	\nearrow	2.0720	\nearrow	2.3822
$n(r_{Ga})=4.1748$							
$\kappa(N, r_{Ga})$	1.5212	\searrow	1.2851	\searrow	0.7814	\searrow	0.411
$\varepsilon_1(N, r_{Ga})$	15.115	\nearrow	15.777	\nearrow	16.818	\nearrow	17.260
$\varepsilon_2(N, r_{Ga})$	12.701	\searrow	10.730	\searrow	6.524	\searrow	3.429
$\sigma_0(N, r_{Ga})$ in $10^2 \Omega^{-1}cm^{-1}$	4.3503	\searrow	3.6750	\searrow	2.234	\searrow	1.174
$\propto (N, r_{Ga})$ in $10^5 cm^{-1}$	4.9331	\searrow	4.1673	\searrow	2.534	\searrow	1.332
$R(N, r_{Ga})$	0.426	\searrow	0.4116	\searrow	0.3903	\searrow	0.380
<hr/>							
$\mathbb{E}_{gp1}(N^*, r_{In}, 20K)$ in eV	1.6184	\nearrow	1.7447	\nearrow	2.0606	\nearrow	2.3683
$n(r_{In})=4.1086$							
$\kappa(N, r_{In})$	1.5359	\searrow	1.3005	\searrow	0.797	\searrow	0.425
$\varepsilon_1(N, r_{In})$	14.522	\nearrow	15.189	\nearrow	16.245	\nearrow	16.700
$\varepsilon_2(N, r_{In})$	12.621	\searrow	10.687	\searrow	6.551	\searrow	3.490
$\sigma_0(N, r_{In})$ in $10^2 \Omega^{-1}cm^{-1}$	4.323	\searrow	3.660	\searrow	2.244	\searrow	1.195
$\propto (N, r_{In})$ in $10^5 cm^{-1}$	4.981	\searrow	4.217	\searrow	2.585	\searrow	1.377
$R(N, r_{In})$	0.422	\searrow	0.409	\searrow	0.385	\searrow	0.375
<hr/>							
$N (10^{18} cm^{-3})$	15		26		60		100
<hr/>							

5.4. Variations of various optical coefficients as functions of T, typically for some d(a)- InP systems

Here, from Equations (24, 28, 29), we can determine the variations of various optical coefficients at $N = 1.5 \times 10^{19} cm^{-3}$, respectively, as functions of T, typically for E=3.2 eV and for some (P, Te, Sn)- InP

systems and (Ga, In)- InP ones, being indicated by the arrows: ↗ and ↘, as given in following Tables 6n and 6p, in which their variations thus depend on the ones of the optical band gap, $\mathbb{E}_{\text{gn1(gp1)}}(N^*, r_{\text{d(a)}})$.

Table 6n. In (P, Te, Sn)-InP systems, our numerical results of the following optical coefficients, expressed as functions of T, and calculated using Equations (31-36, 24), for $E=3.2$ eV and $N = 1.5 \times 10^{19} \text{ cm}^{-3}$, increase with increasing T, since the optical band gap $\mathbb{E}_{\text{gn1}}(T, r_{\text{d}})$ decreases with increasing T.

T in K		20	30	50	100	200	300
$\mathbb{E}_{\text{gn}} \equiv \mathbb{E}_{\text{gn1}}(T, r_{\text{p}})$ in eV	↘	1.6714	1.6708	1.6688	1.6608	1.6358	1.6039
$n(r_{\text{p}}, T)$	↗	4.109	4.1094	4.1119	4.1218	4.1529	4.193
$\kappa(r_{\text{p}}, T)$	↗	1.435	1.436	1.440	1.455	1.502	1.564
$\varepsilon_1(r_{\text{p}}, T)$	↗	14.823	14.826	14.835	14.873	14.989	15.134
$\varepsilon_2(r_{\text{p}}, T)$	↗	11.789	11.802	11.839	11.993	12.478	13.117
$\sigma_{\text{O}}(r_{\text{p}}, T)$ in $10^2 \Omega^{-1} \text{cm}^{-1}$	↗	4.038	4.042	4.055	4.108	4.274	4.493
$\alpha(r_{\text{p}}, T)$ in 10^5cm^{-1}	↗	4.652	4.656	4.668	4.718	4.872	5.072
$R(r_{\text{p}}, T)$	↗	0.416	0.4164	0.4168	0.418	0.423	0.430
$\mathbb{E}_{\text{gn}} \equiv \mathbb{E}_{\text{gn1}}(T, r_{\text{Te}})$ in eV	↘	1.6571	1.6565	1.6545	1.6465	1.6215	1.5896
$n(r_{\text{Te}}, T)$	↗	3.969	3.970	3.973	3.983	4.014	4.054
$\kappa(r_{\text{Te}}, T)$	↗	1.462	1.463	1.467	1.482	1.530	1.592
$\varepsilon_1(r_{\text{Te}}, T)$	↗	13.620	13.623	13.631	13.665	13.769	13.897
$\varepsilon_2(r_{\text{Te}}, T)$	↗	11.604	11.616	11.653	11.804	12.282	12.910
$\sigma_{\text{O}}(r_{\text{Te}}, T)$ in $10^2 \Omega^{-1} \text{cm}^{-1}$	↗	3.974	3.979	3.991	4.043	4.206	4.422
$\alpha(r_{\text{Te}}, T)$ in 10^5cm^{-1}	↗	4.740	4.744	4.756	4.806	4.961	5.164
$R(r_{\text{Te}}, T)$	↗	0.408	0.4084	0.4088	0.4105	0.4157	0.422
$\mathbb{E}_{\text{gn}} \equiv \mathbb{E}_{\text{gn1}}(T, r_{\text{Sn}})$ in eV	↘	1.6471	1.6465	1.6445	1.6365	1.6115	1.5796
$n(r_{\text{Sn}}, T)$	↗	3.877	3.878	3.880	3.890	3.921	3.961
$\kappa(r_{\text{Sn}}, T)$	↗	1.481	1.482	1.486	1.501	1.549	1.612
$\varepsilon_1(r_{\text{Sn}}, T)$	↗	12.837	12.840	12.847	12.879	12.974	13.091
$\varepsilon_2(r_{\text{Sn}}, T)$	↗	11.481	11.493	11.529	11.678	12.151	12.772
$\sigma_{\text{O}}(r_{\text{Sn}}, T)$ in $10^2 \Omega^{-1} \text{cm}^{-1}$	↗	3.932	3.936	3.949	4.000	4.162	4.375
$\alpha(r_{\text{Sn}}, T)$ in 10^5cm^{-1}	↗	4.802	4.806	4.818	4.868	5.024	5.228
$R(r_{\text{Sn}}, T)$	↗	0.403	0.4032	0.4036	0.4053	0.4108	0.4177
T in K		20	30	50	100	200	300

Table 6p. In (Ga, In)-InP systems, our numerical results of the following optical coefficients, expressed as functions of T, and calculated using Equations (31-36, 24), for $E=3.2$ eV and $N = 1.5 \times 10^{19} \text{ cm}^{-3}$, increase with increasing T, since the optical band gap $\mathbb{E}_{\text{gp1}}(T, r_{\text{a}})$ decreases with increasing T.

T in K		20	30	50	100	200	300
$\mathbb{E}_{\text{gp}} \equiv \mathbb{E}_{\text{gp1}}(T, r_{\text{Ga}})$ in eV	↘	1.6260	1.6254	1.6234	1.6154	1.5905	1.5587

$n(r_{Ga}, T)$	\nearrow	4.175	4.1756	4.178	4.188	4.219	4.259
$\kappa(r_{Ga}, T)$	\nearrow	1.521	1.522	1.526	1.542	1.591	1.654
$\varepsilon_1(r_{Ga}, T)$	\nearrow	15.115	15.117	15.126	15.161	15.270	15.404
$\varepsilon_2(r_{Ga}, T)$	\nearrow	12.701	12.714	12.754	12.914	13.422	14.090
$\sigma_O(r_{Ga}, T)$ in $10^2 \Omega^{-1}cm^{-1}$	\nearrow	4.350	4.355	4.368	4.423	4.597	4.826
$\alpha(r_{Ga}, T)$ in $10^5 cm^{-1}$	\nearrow	4.933	4.937	4.949	5.000	5.158	5.364
$R(r_{Ga}, T)$	\nearrow	0.426	0.4261	0.4265	0.428	0.433	0.439
<hr/>							
$\mathbb{E}_{gp} \equiv \mathbb{E}_{gp1}(T, r_{In})$ in eV	\searrow	1.6184	1.6178	1.6158	1.6078	1.5829	1.5512
<hr/>							
$n(r_{In}, T)$	\nearrow	4.109	4.1094	4.112	4.122	4.153	4.193
$\kappa(r_{In}, T)$	\nearrow	1.536	1.537	1.541	1.557	1.606	1.669
$\varepsilon_1(r_{In}, T)$	\nearrow	14.522	14.524	14.533	14.566	14.668	14.794
$\varepsilon_2(r_{In}, T)$	\nearrow	12.621	12.634	12.673	12.833	13.337	13.999
$\sigma_O(r_{In}, T)$ in $10^2 \Omega^{-1}cm^{-1}$	\nearrow	4.323	4.327	4.341	4.395	4.568	4.795
$\alpha(r_{In}, T)$ in $10^5 cm^{-1}$	\nearrow	4.981	4.985	4.997	5.048	5.207	5.414
$R(r_{In}, T)$	\nearrow	0.422	0.4226	0.423	0.4247	0.4298	0.436
<hr/>							
T in K		20	30	50	100	200	300

6. Concluding remarks

In the n(p)-type degenerate InP-crystal, by using the same physical model, as that given in Eq. (7), and same mathematical methods, as those proposed in I, II and III, and further, by taking into account the corrected values of energy-band-structure parameters, and mainly the correct asymptotic behaviors of the refraction index n and extinction coefficient κ , as the photon energy $E(\rightarrow \infty)$, all the numerical results, obtained in III, are now revised and performed.

So, by basing on our following basic expressions, as:

- (i) the effective static dielectric constant, $\varepsilon(r_{d(a)})$, due to the impurity size effect, determined by an effective Bohr model [1], and given in Eq. (2),
- (ii) the critical donor(acceptor)-density, $N_{CDn(NDp)}(r_{d(a)})$, determined from the generalized effective Mott criterion in the MIT, and as given in Eq. (3), being used to determine the effective d(a)-density: $N^* \equiv N - N_{CDn(CDp)}(r_{d(a)})$, which gives a physical condition, needed to define the metal-insulator transition (**MIT**) at $T=0K$, as: $N^* \equiv N - N_{CDn(CDp)} = 0$ or $N = N_{CDn(CDp)}$, noting that $N_{CDn(CDp)}$ can also be explained as the density of electrons(holes) localized in the exponential conduction(valence)-band tails (EBT), $N_{CDn(CDp)}^{EBT}$, as that determined in Eq. (21), with a precision of the order of 7.61×10^{-4} , as observed in Table 1,
- (iii) the Fermi energy, $E_{Fn(Fp)}(N^*, T)$, determined in Eq. (A3) of the Appendix A, with a precision of the order of 2.11×10^{-4} [3], and finally,
- (iv) the refraction index n and the extinction coefficient κ , determined in Equations (28, 29), verifying their correct asymptotic behaviors,

we have investigated the optical coefficients, determined from Equations (24, 25, 28, 29), and their numerical results, given in different physical conditions, have been obtained and discussed in above Tables 2a, 2b, 2c, 3a, 3b, 3c, 4n(4p), 5n(5p), and finally 6n(6p). In particular, in Tables 3a, 3b and 3c, our numerical results for those optical coefficients are found to be more accurate than the corresponding ones, calculated from the FB-PM [11].

Finally, one notes that the MIT occurs in the degenerate case, in which:

(a) $\mathbb{E}_{\text{Fn}(\text{Fpo})}(N^* = 0, T = 0) = 0$, determined by Eq. (A4) of the Appendix A, since it is proportional to $(N^*)^{2/3}$,

(b) as discussed in Eq. (5), in the MIT, in which $\mathbb{E}_{\text{gn1}(\text{gp1})}(N^* = 0, r_{\text{d(a)}}, T = 0) = \mathbb{E}_{\text{gni}(\text{gpi})}(r_{\text{d(a)}})$,

where $\mathbb{E}_{\text{gn1}(\text{gp1})}$ and $\mathbb{E}_{\text{gni}(\text{Fgpi})}$ are the optical band gap and intrinsic band gap, respectively, and

(c) as discussed in Section 5.1, as $E = E_{\text{CPE}}(r_{\text{d(a)}}) \equiv \mathbb{E}_{\text{gni}(\text{gpi})}(r_{\text{d(a)}})$ or the effective photon energy $E^* \equiv E - \mathbb{E}_{\text{gni}(\text{gpi})}(r_{\text{d(a)}}) = 0$, one has: $\kappa(E^* = 0, r_{\text{d(a)}}) = 0$, $\varepsilon_2(E^* = 0, r_{\text{d(a)}}) = 0$, $\sigma_0(E^* = 0, r_{\text{d(a)}}) = 0$ and $\alpha(E^* = 0, r_{\text{d(a)}}) = 0$, according also to the MIT-case, being new results.

In summary, all the numerical results, given in III [3], are now revised and performed in the present work.

Appendix

Appendix A. Fermi Energy and generalized Einstein relation

A1. In the n(p)-type InP-crystals, the Fermi energy $\mathbb{E}_{\text{Fn}(\text{Fp})} \equiv [\mathbb{E}_{\text{fn}} - \mathbb{E}_{\text{c}}](\mathbb{E}_{\text{Fp}} \equiv [\mathbb{E}_{\text{v}} - \mathbb{E}_{\text{fp}}])$, $\mathbb{E}_{\text{c(v)}}$ being the conduction (valence) band edges, obtained for any T and donor (acceptor) density N, being investigated in our previous paper, with a precision of the order of 2.11×10^{-4} [3], is now summarized in the following. In this work, N is replaced by the effective density N^* , $N^* \equiv N - N_{\text{CDn}(\text{CDp})}(r_{\text{d(a)}})$, $N_{\text{CDn}(\text{CDp})}(r_{\text{d(a)}})$ being the critical density, being characteristic of the MIT-phenomenon, and their numerical results are given in Table 1, meaning that $N^* = 0$ at this transition.

First, we define the reduced electron density by:

$$u(N^*, r_{\text{d(a)}}, T) \equiv u(N^*, T) \equiv \frac{N^*}{N_{\text{c(v)}}}, N_{\text{c(v)}}(T) = 2 \times g_{\text{c(v)}} \times \left(\frac{m_{\text{n(p)}}^* \times k_{\text{B}} T}{2\pi\hbar^2} \right)^{\frac{3}{2}} (\text{cm}^{-3}), \quad (\text{A1})$$

where $N_{\text{c(v)}}(T)$ is the conduction (valence)-band density of states, the values of $g_{\text{c(v)}} (= 1)$, and $m_{\text{n(p)}}^*/m_0$, defined in Section 2, can be equal to : $m_{\text{n(p)}}/m_0 = 0.073$ (0.339), and to $m_{\text{r}}/m_0 = \frac{m_{\text{n}} \times m_{\text{p}}}{m_{\text{n}} + m_{\text{p}}} = 0.06$. In particular, as used in Section 3 for determining the optical band gap in degenerate InP-crystals, $m_{\text{n(p)}}^*/m_0 = m_{\text{r}}/m_0 = 0.06$ was chosen. Then, the reduced Fermi energy in the n(p)-type GaAs is determined by :

$$\frac{\mathbb{E}_{\text{Fn}}(u)}{k_{\text{B}} T} \left(\frac{\mathbb{E}_{\text{Fp}}(u)}{k_{\text{B}} T} \right) = \frac{G(u) + A u^B F(u)}{1 + A u^B} = \theta_{\text{n}}(u) \equiv \frac{V(u)}{W(u)}, A = 0.0005372 \text{ and } B = 4.82842262, \quad (\text{A2})$$

where $F(N^*, r_{\text{d(a)}}, T) = a u^{\frac{2}{3}} \left(1 + b u^{-\frac{4}{3}} + c u^{-\frac{8}{3}} \right)^{-\frac{2}{3}}$, obtained for $u \gg 1$, according to the degenerate cas,

$a = [(3\sqrt{\pi}/4)]^{2/3}$, $b = \frac{1}{8}(\frac{\pi}{a})^2$, $c = \frac{62.3739855}{1920}(\frac{\pi}{a})^4$, and then $G(u) \simeq \text{Ln}(u) + 2^{-\frac{3}{2}} \times u \times e^{-du}$ for $u \ll 1$, according to the non – degenerate case, with: $d = 2^{3/2} \left[\frac{1}{\sqrt{27}} - \frac{3}{16} \right] > 0$.

So, in the present degenerate case ($u \gg 1$), one has:

$$\mathbb{E}_{\text{Fn}(\text{Fp})}(N^*, r_{d(a)}, T) \equiv \mathbb{E}_{\text{Fn}(\text{Fp})}(N^*, T) = \mathbb{E}_{\text{Fno}(\text{Fpo})}(u) \times \left(1 + bu^{-\frac{4}{3}} + cu^{-\frac{8}{3}} \right)^{\frac{2}{3}}. \quad (\text{A3})$$

Then, at $T=0\text{K}$, since $u^{-1} = 0$, Eq. (A.3) is reduced to:

$$\mathbb{E}_{\text{Fno}(\text{Fpo})}(N^*) \equiv \frac{\hbar^2 \times k_{\text{Fn}(\text{Fp})}^2(N^*)}{2 \times m_{n(p)}^*}, \quad (\text{A4})$$

being proportional to $(N^*)^{2/3}$, and equal to 0, $\mathbb{E}_{\text{Fno}(\text{Fpo})}(N^* = 0) = 0$, according to the MIT, as discussed in Section 2 and 3.

Appendix B. Approximate forms for band gap narrowing (BGN)

First of all, in the n(p)-type InP-crystals, we define the effective reduced Wigner-Seitz radius $r_{\text{sn}(\text{sp})}$, characteristic of the interactions, by:

$$r_{\text{sn}(\text{sp})}(N^*, r_{d(a)}) \equiv \left(\frac{3g_c(v)}{4\pi N^*} \right)^{1/3} \times \frac{1}{a_{\text{Bn}(\text{Bp})}(r_{d(a)})} = 1.1723 \times 10^8 \times \left(\frac{g_c(v)}{N^*} \right)^{1/3} \times \frac{m_{n(p)}^*/m_0}{\varepsilon(r_{d(a)})}. \quad (\text{B1})$$

In particular, in the following, $m_{n(p)}^*/m_0 = m_r/m_0$, is taken for evaluating the band gap narrowing (BGN), as used in Section 3. Therefore, the correlation energy of an effective electron gas, $\mathbb{E}_{\text{CE}}(r_{\text{sn}(\text{sp})})$, is found to be given by [1]:

$$\mathbb{E}_{\text{CE}}(r_{\text{sn}(\text{sp})}) \equiv \mathbb{E}_{\text{CE}}(N^*, r_{d(a)}) = \frac{-0.87553}{0.0908 + r_{\text{sn}(\text{sp})}} + \frac{\frac{0.87553}{0.0908 + r_{\text{sn}(\text{sp})}} + \left(\frac{2[1 - \ln(2)]}{\pi^2} \right) \times \ln(r_{\text{sn}(\text{sp})}) - 0.093288}{1 + 0.03847728 \times r_{\text{sn}(\text{sp})}^{1.67378876}}. \quad (\text{B2})$$

Then, the band gap narrowing (BGN) can be determined by [1]:

$$\Delta \mathbb{E}_{\text{gn}}(N^*, r_d) \simeq a_1 \times \frac{\varepsilon_0}{\varepsilon(r_d)} \times N_r^{1/3} + a_2 \times \frac{\varepsilon_0}{\varepsilon(r_d)} \times N_r^{1/3} \times (2.503 \times [-\mathbb{E}_{\text{CE}}(r_{\text{sn}}) \times r_{\text{sn}}]) + a_3 \times \left[\frac{\varepsilon_0}{\varepsilon(r_d)} \right]^{5/4} \times \sqrt{\frac{m_p}{m_r}} \times N_r^{1/4} + a_4 \times \sqrt{\frac{\varepsilon_0}{\varepsilon(r_d)}} \times N_r^{1/2} \times 2 + a_5 \times \left[\frac{\varepsilon_0}{\varepsilon(r_d)} \right]^{3/2} \times N_r^{1/6}, \quad (\text{B3})$$

$N_r \equiv \frac{N^* = N - N_{\text{CDn}}(r_d)}{9.999 \times 10^{17} \text{ cm}^{-3}},$

where $\varepsilon_0 = \varepsilon_p = 12.5$, $a_1 = 6.8286 \times 10^{-3}(\text{eV})$, $a_2 = 1.1681 \times 10^{-3}(\text{eV})$, $a_3 = 5.0316 \times 10^{-3}(\text{eV})$, $a_4 = 10.1 \times 10^{-3}(\text{eV})$ and $a_5 = 1.4556 \times 10^{-3}(\text{eV})$, and

$$\Delta \mathbb{E}_{\text{gp}}(N^*, r_a) \simeq a_1 \times \frac{\varepsilon_0}{\varepsilon(r_a)} \times N_r^{1/3} + a_2 \times \frac{\varepsilon_0}{\varepsilon(r_a)} \times N_r^{1/3} \times (2.503 \times [-\mathbb{E}_{\text{CE}}(r_{\text{sp}}) \times r_{\text{sp}}]) + a_3 \times \left[\frac{\varepsilon_0}{\varepsilon(r_a)} \right]^{5/4} \times \sqrt{\frac{m_n}{m_r}} \times N_r^{1/4} + 2a_4 \times \sqrt{\frac{\varepsilon_0}{\varepsilon(r_a)}} \times N_r^{1/2} + a_5 \times \left[\frac{\varepsilon_0}{\varepsilon(r_a)} \right]^{3/2} \times N_r^{1/6}, \quad (\text{B4})$$

$N_r \equiv \left(\frac{N^* = N - N_{\text{CDp}}(r_a)}{9.999 \times 10^{17} \text{ cm}^{-3}} \right),$

where $\varepsilon_0 = \varepsilon_{\text{In}} = 12.5$, $a_1 = 9.329 \times 10^{-3}(\text{eV})$, $a_2 = 1.5958 \times 10^{-3}(\text{eV})$, $a_3 = 7.1441 \times 10^{-3}(\text{eV})$, $a_4 = 13.7 \times 10^{-3}(\text{eV})$ and $a_5 = 1.9886 \times 10^{-3}(\text{eV})$.

Therefore, in Equations (B3, B4), at $T=0 \text{ K}$ and $N^* = 0$, and for any $r_{d(a)}$, $\Delta \mathbb{E}_{\text{gn}(\text{gp})}(N^* = 0, r_{d(a)}) = 0$, according to the MIT.

References

- [1] H. Van Cong, “New dielectric constant, due to the impurity size effect, and determined by an effective Bohr model, affecting strongly the Mott criterion in the metal-insulator transition and the optical band gap in degenerate (Si, GaAs, InP)-semiconductors,” *SCIREA J. Phys.*, vol.7, pp. 221-234 (2022).
- [2] H. Van Cong, “ Same maximum figure of merit $ZT(=1)$, due to effects of impurity size and heavy doping, obtained in the n(p)-type degenerate InP-crystal ($\xi_{n(p)}(\geq 1)$), at same reduced Fermi energy $\xi_{n(p)} (= 1.813)$ and same minimum (maximum) Seebeck coefficient $S_b (= (\mp)1.563 \times 10^{-4} \frac{V}{K})$, at which same

$$(ZT)_{\text{Mott}} (= \frac{\pi^2}{3 \times \xi_{n(p)}^2} \simeq 1)$$
 , “*SCIREA J. Phys.*, vol.8, pp. 91-114 (2023).
- [3] H. Van Cong, “Effects of donor size and heavy doping on optical, electrical and thermoelectric properties of various degenerate donor-silicon systems at low temperatures,” *American Journal of Modern Physics*, vol. 7, pp. 136-165 (2018); “Accurate expressions for optical coefficients, due to the impurity-size effect, and obtained in n(p)-type degenerate Si crystals, taking into account their correct asymptotic behavior, as the photon energy $E (\rightarrow \infty)$,” *SCIREA J. Phys.*, vol.8, pp. 172-197 (2023).
- [4] H. Van Cong et al., “A simple accurate expression of the reduced Fermi energy for any reduced carrier density. *J. Appl. Phys.*, vol. 73, pp. 1545-15463, 1993; H. Van Cong and B. Doan Khanh, “Simple accurate general expression of the Fermi-Dirac integral $F_j(a)$ and for $j > -1$,” *Solid-State Electron.*, vol. 35, pp. 949-951(1992); H. Van Cong, “New series representation of Fermi-Dirac integral $F_j(-\infty < a < \infty)$ for arbitrary $j > -1$, and its effect on $F_j(a \geq 0_+)$ for integer $j \geq 0$,” *Solid-State Electron.*, vol. 34, pp. 489-492 (1991).
- [5] C. Kittel, “Introduction to Solid State Physics, pp. 84-100. Wiley, New York (1976).
- [6] M. A. Green, “Intrinsic concentration, effective density of states, and effective mass in silicon,” *J. Appl. Phys.*, vol. 67, 2944-2954 (1990).
- [7] H. Van Cong et al., “Optical bandgap in various impurity-Si systems from the metal-insulator transition study,” *Physica B*, vol. 436, pp. 130-139, 2014; H. Stupp et al., *Phys. Rev. Lett.*, vol. 71, p. 2634 (1993); P. Dai et al., *Phys. Rev. B*, vol. 45, p. 3984 (1992).
- [8] J. Wagner and J. A. del Alamo, *J. Appl. Phys.*, vol. 63, 425-429 (1988).
- [9] D. E. Aspnes, A. A. Studna, “Dielectric functions and optical parameters of Si, Se, GaP, GaAs, GaSb, InP, InAs, and InSb from 1.5 to 6.0 eV”, *Phys. Rev. B*, vol. 27, 985-1009 (1983).
- [10] L. Ding, et al., “Optical properties of silicon nanocrystals embedded in a SiO_2 matrix”, *Phys. Rev. B*, vol. 72, 125419 (2005).
- [11] A. R. Forouhi, I. Bloomer, “Optical properties of crystalline semiconductors and dielectrics”, *Phys. Rev.*, vol. 38, 1865-1874 (1988).
- [12] G. E. Jr. Jellison, F. A. Modine, “Parameterization of the optical functions of amorphous materials in the inter-band region”, *Appl. Phys. Lett.*, vol. 69, 371-373 (1996).